


## **OIL ANALYSIS REPORT**

# SSR ULTRA COOLANT INGERSOLL RAND VN1588U13316 - TERMINAL RAILROAD

Component







## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

## **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

0.4.4.D. E. IV.E.O.D.								
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		UCH06123793	UCH06061306			
Sample Date		Client Info		07 Mar 2024	08 Jan 2024			
Machine Age	hrs	Client Info		73189	72225			
Oil Age	hrs	Client Info		4302	3348			
Oil Changed		Client Info		Not Changd	Not Changd			
Sample Status				NORMAL	NORMAL			
CONTAMINATION	V	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG			
WEAR METALS		method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>50	<1	1			
Chromium	ppm		>10	0	<1			
Nickel	ppm	ASTM D5185m	7.0	0	0			
Titanium	ppm	ASTM D5185m		0	<1			
Silver	ppm	ASTM D5185m		0	0			
Aluminum	ppm	ASTM D5185m	>25	0	2			
Lead	ppm	ASTM D5185m	>25	0	0			
Copper	ppm	ASTM D5185m	>50	0	<1			
Tin	ppm	ASTM D5185m	>15	0	<1			
Vanadium	ppm	ASTM D5185m		0	0			
Cadmium	ppm	ASTM D5185m		0	0			
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m	0	0	0			
Barium	ppm	ASTM D5185m	500	681	628			
Molybdenum	ppm	ASTM D5185m	0	0	0			
Manganese	ppm	ASTM D5185m		0	0			
Magnesium	ppm	ASTM D5185m	0	0	0			
Calcium	ppm	ASTM D5185m	0	1	2			
Phosphorus	ppm	ASTM D5185m	20	0	34			
Zinc	ppm	ASTM D5185m	0	0	0			
Sulfur	ppm	ASTM D5185m	200	386	261			
CONTAMINANTS	;	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>25	0	<1			
Sodium	ppm	ASTM D5185m		22	25			
Potassium	ppm	ASTM D5185m	>20	2	2			
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2		
Acid Number (AN)	mg KOH/g	ASTM D8045		0.269	0.17			



St

## **OIL ANALYSIS REPORT**




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPER	HES	method			history1	history2
Visc @ 40°C	cSt	ASTM D445	49.4	51.7	52.0	

Or tivil LL livir tale			
Color			no image
Bottom			no image

## **GRAPHS**



10 T =	on-1	terr	ou	S	M	et	a	ls													
8 - 5		naan je	opper																		
mdd 4	*****	mana tj	n	)																	
4																					
2				-			100		-	-	_		-	-	-	 -	-	-	_	-	-
Jan8/24		******							 	 		-			-		 -		-		Mar7/24
Ja																					Ma









Certificate L2367

Laboratory Sample No. Lab Number : 06123793

Test Package : IND 2

: UCH06123793 Unique Number : 10937944

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

: 20 Mar 2024 : 21 Mar 2024

: 22 Mar 2024 - Don Baldridge Diagnosed

JOHN HENRY FOSTER COMPANY

4700 LEBOURGET STREET SAINT LOUIS, MO

US 63134

Contact: RACHEL VON HATTEN

rvonhatten@jhf.com T: (314)593-1267

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (314)874-0965

Contact/Location: RACHEL VON HATTEN - UCJOHSAI