

### **OIL ANALYSIS REPORT**

## SMART OIL Machine Id HERTZ VD032002

Component

Compressor

SMARTOIL 6000 (3 GAL)

# Sample Rating Trend



#### DIAGNOSIS

#### Recommendation

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

Moderate concentration of visible dirt/debris present in the oil.


#### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	/ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06123832		
Sample Date		Client Info		07 Mar 2024		
Machine Age	hrs	Client Info		1639		
Oil Age	hrs	Client Info		1639		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	4		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	. 10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	8		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m	710	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m	20	0		
Phosphorus	ppm	ASTM D5185m		53		
Zinc	ppm	ASTM D5185m		10		
Sulfur	ppm	ASTM D5185m		486		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	2		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.203		




### **OIL ANALYSIS REPORT**




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	MODER		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.5		


SAMPLE IMAGES	method	limit/base	current	history1	history2
Color		a		no image	no image
Bottom				no image	no image

#### **GRAPHS**



	0	Non-ferrous Metals	
- 1	UΤ		
	8	copper	
	٥Ť	neanananana  ead	
	61	programme tin	
mdd	٩T		
	4	1	
	1		
	2+		
	0 T		-
		Mar7/24	
		Mar7/2.	
		ž	









Certificate L2367

Laboratory Sample No. Unique Number : 10937983

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Test Package : IND 2

: UHK06123832 Lab Number : 06123832

Received **Tested** 

Diagnosed

: 20 Mar 2024 : 21 Mar 2024

: 22 Mar 2024 - Don Baldridge

ATLANTA AIR COMPRESSOR - HERTZ

123 MERCHANTS PARK DR HOSCHTON, GA US 30548

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: