

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id **122201** Component Hydraulic System Fluid

MOBIL DTE 10 EXCEL 46 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The condition of the oil is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0005786		
Sample Date		Client Info		14 Mar 2024		
Machine Age	hrs	Client Info		4242		
Oil Age	hrs	Client Info		4242		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIC	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	4		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	0		
Lead	ppm	ASTM D5185m	>20	<1		
Copper	ppm	ASTM D5185m	>20	2		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		61		
Phosphorus	ppm	ASTM D5185m		360		
Zinc	ppm	ASTM D5185m		385		
Sulfur	ppm	ASTM D5185m		1183		
CONTAMINANT	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	3		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
3:56:07) Rev: 1					Submitted By	: Loren Michael



OIL ANALYSIS REPORT

Viscosity @ 40°C



FLUID PROPERT	TES me	ethod				history2
Visc @ 40°C	cSt AST	M D445	45.6	42.3		
SAMPLE IMAGES	S me	ethod	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS					1	
Ferrous Alloys			Mar14/24 Mar14/24 Mar14/24			
: WearCheck USA - 50 : SBP0005786 : 06124440 : 10938591 : FLEET contact Customer Serve	Received Tested Diagnosed	:20 :21 d:23	Mar 2024 Mar 2024 Mar 2024 - Dor	n Baldridge		s Inc 60365 1815 Y Stre Lincoln, N US 6850 : Loren Micha

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

F:

T: (402)434-2157