

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area AS-IR [1499] Machine Id SULLAIR 201501210026 - HOFFMAN ENCLOSURES Component

Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Feb2024		
SAMPLE INFORM	ΛΑΤΙΟΝ	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06124982		
Sample Date		Client Info		07 Feb 2024		
Machine Age	hrs	Client Info		56421		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	3		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		6		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		3		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		345		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3		
Sodium	ppm	ASTM D5185m		120		
Potassium	ppm	ASTM D5185m	>20	38		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.29		



0.30 0.30 0.024 0.024 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.00 0.024 0.

52 Abnormal

> ²⁸ Feb7/24

Acid Number

Viscosity @ 40°C

OIL ANALYSIS REPORT

	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	LIGHT		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Feb1/24	Appearance	scalar	*Visual	NORML	NORML		
L.	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
1	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		47.9		
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Feb7/24	Color					no image	no image
	Bottom					no image	no image
	pmm Feb7/24 Feb7/24			Feb7/24			
	Non-ferrous Metal	S		Feb7/24			
	Viscosity @ 40°C				Acid Number		
	50 +			2			
	50			0. 	UU		
	50 + 7 ♀ 45 - 45 - 40 - Abnormal			Feb7/24			Ear17/24

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: UCAIRDEE [WUSCAR] 06124982 (Generated: 03/24/2024 13:17:28) Rev: 1

Contact/Location: AARON RIOS - UCAIRDEE

F: