


OIL ANALYSIS REPORT

Area [134442] RED VENTURES/RV4-ACD3 UNIT B

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)





Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| Jan 2021 Fab 2022 Mag 2023 Mag 2024 | | | | | | | | |
|-------------------------------------|----------|-------------|------------|-------------|-------------|-------------|--|--|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 | | |
| Sample Number | | Client Info | | WC0770515 | WC0770431 | WC0637147 | | |
| Sample Date | | Client Info | | 05 Mar 2024 | 28 Mar 2023 | 02 Feb 2022 | | |
| Machine Age | hrs | Client Info | | 103 | 101 | 96 | | |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 | | |
| Oil Changed | | Client Info | | Changed | Changed | Changed | | |
| Sample Status | | | | NORMAL | NORMAL | NORMAL | | |
| CONTAMINATION | ٧ | method | limit/base | current | history1 | history2 | | |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 | | |
| Water | | WC Method | >0.2 | NEG | NEG | NEG | | |
| Glycol | | WC Method | | NEG | NEG | NEG | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 | | |
| Iron | ppm | ASTM D5185m | >100 | <1 | <1 | 2 | | |
| Chromium | ppm | ASTM D5185m | >20 | <1 | 0 | 0 | | |
| Nickel | ppm | ASTM D5185m | >4 | 0 | 0 | <1 | | |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | 1 | | |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 | | |
| Aluminum | ppm | ASTM D5185m | >20 | <1 | 0 | <1 | | |
| Lead | ppm | ASTM D5185m | >40 | 0 | 0 | <1 | | |
| Copper | ppm | ASTM D5185m | >330 | 1 | 0 | 1 | | |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | 0 | | |
| Antimony | ppm | ASTM D5185m | | | | <1 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | <1 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 | | |
| Boron | ppm | ASTM D5185m | 250 | 14 | 73 | 87 | | |
| Barium | ppm | ASTM D5185m | 10 | 0 | 0 | 0 | | |
| Molybdenum | ppm | ASTM D5185m | 100 | 58 | 21 | 10 | | |
| Manganese | ppm | ASTM D5185m | | <1 | 0 | <1 | | |
| Magnesium | ppm | ASTM D5185m | 450 | 907 | 704 | 745 | | |
| Calcium | ppm | ASTM D5185m | 3000 | 1026 | 1129 | 1257 | | |
| Phosphorus | ppm | ASTM D5185m | 1150 | 995 | 954 | 967 | | |
| Zinc | ppm | ASTM D5185m | 1350 | 1185 | 1100 | 1120 | | |
| Sulfur | ppm | ASTM D5185m | 4250 | 3499 | 3528 | 3052 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 | | |
| Silicon | ppm | ASTM D5185m | >25 | 5 | 3 | 5 | | |
| Sodium | ppm | ASTM D5185m | >158 | <1 | 0 | 2 | | |
| Potassium | ppm | ASTM D5185m | >20 | 0 | 3 | 3 | | |
| INFRA-RED | | method | limit/base | current | history1 | history2 | | |
| Soot % | % | *ASTM D7844 | >3 | 0 | 0.1 | 0 | | |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 4.6 | 5.5 | 6.1 | | |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 17.0 | 18.2 | 19.8 | | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 | | |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 12.3 | 12.0 | 13.3 | | |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 9.7 | 9.9 | 10.8 | | |



OIL ANALYSIS REPORT



| VISUAL | | method | limit/base | current | history1 | history2 | |
|-------------------------|------------|-----------|------------|---------|----------|----------|--|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE | |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE | |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE | |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE | |
| Debris | scalar | *Visual | NONE | NONE | NONE | LIGHT | |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE | |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML | |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML | |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG | |
| Free Water | scalar | *Visual | | NEG | NEG | NEG | |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 | |
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 13.8 | 14.1 | 14.5 | |
| GRAPHS | | | | | | | |
| Iron (ppm) | Lead (ppm) | | | | | | |

| GRAPH | HS | | | | | | |
|------------------|------------|------------|-----------|-------------------------------|------------|------------|-----------|
| Iron (p | pm) | | | Lead (pp | m) | | |
| 250 Severe | | | | Severe | | | |
| 150 Abnormal | | | | Abnormal | | | |
| 1 | | | | 10 1 | | | |
| 50 | | | | 20 | | | |
| Jan27/21 | Feb2/22 - | Mar28/23 - | Mar5/24 - | Jan27/21 | Feb 2/22 - | Mar28/23 - | Mar5/24 |
| | | Mar | Ma | | | Mar | ĕ |
| Alumin | um (ppm) | | | Chromiui 50 _T : | m (ppm) | | |
| 40 Severe | | | | 40 - Severe | | | |
| Abnormal | | | | Abnormal | | | |
| 10 | | | | 10+ | | | |
| 0 | | | | 0 | | | |
| Jan27/21 | Feb2/22 - | Mar28/23 | Mar5/24 | Jan27/21 | Feb2/22 | Mar28/23 | Mar5/24 |
| Copper | | 2 | | Silicon (p | opm) | 2 | |
| Severe Abnormal | | | | 80 - Severe | | | |
| 300 | | | | 60 | | | |
| 200 | | | | Abnormal | | | |
| 100 | | | | 20+ | : | | |
| 0 12/ | | | 724 | 0 | 722 | /23 | 724 |
| Jan27/21 | Feb2/22 | Mar28/23 | Mar5/24 | Jan27/2' | Feb2/22 | Mar28/23 | Mar5/24 - |
| Viscosit | ty @ 100°C | | | Base Nur | mber | | |
| Abnormal | | | | Abnormal | | ! | |
| Base Abnormal | | | | Base Base | | | |
| Abnormal | | | | Abnormal Base 5.0 Abnormal | | | |
| 10 | | | | 0.0 Base | | | |
| Jan27/21 | Feb2/22 - | Mar28/23 + | Mar5/24 | Jan27/21 | Feb2/22 - | Mar28/23 + | Mar5/24 |
| Jan | 並 | Marž | Ma | Jan | Ē | Marź | Ma |





Laboratory

Unique Number : 10939691

Sample No. : WC0770515 Lab Number : 06125540

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Tested

Diagnosed Test Package: MOB 1 (Additional Tests: TBN)

: 21 Mar 2024 : 22 Mar 2024

: 22 Mar 2024 - Wes Davis

4541 PRESLYN DR RALEIGH, NC US 27616 Contact: BRANDON RICE

NATIONAL POWER CORP

brandon.rice@natpow.com T:

Contact/Location: BRANDON RICE - NATRAL

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (919)790-9714