

OIL ANALYSIS REPORT

Area **EG10/LYOS** [3096880] Machine Id **14AR03** Component

Refrigeration Compressor Fluid CPI SOLEST 68 (4 GAL)

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is a trace of moisture present in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.





SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0907794	WC0871237	WC0840227
Sample Date		Client Info		25 Mar 2024	21 Dec 2023	06 Oct 2023
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	N/A	Not Changd
Sample Status				MARGINAL	MARGINAL	MARGINAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	18	11	11
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		0	<1	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	1	<1	0
Lead	ppm	ASTM D5185m	>2	0	2	<1
Copper	ppm	ASTM D5185m		64	43	41
Tin	ppm	ASTM D5185m	>4	<1	1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		0	2	0
Magnesium	ppm	ASTM D5185m		<1	<1	<1
Calcium	ppm	ASTM D5185m		7	<1	0
Phosphorus	ppm	ASTM D5185m		3	10	3
Zinc	ppm	ASTM D5185m		12	4	4
Sulfur	ppm	ASTM D5185m		0	0	38
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	3	2	2
Sodium	ppm	ASTM D5185m		1	2	0
Potassium	ppm	ASTM D5185m	>20	<1	3	<1
Water	%	ASTM D6304	>0.01	A 0.021	▲ 0.010	▲ 0.015
ppm Water	ppm	ASTM D6304	>100	A 212	1 01	▲ 153.8
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	1102	2197	1589
Particles >6µm		ASTM D7647	>2500	152	816	267
Particles >14µm		ASTM D7647	>320	6	70	17
Particles >21µm		ASTM D7647	>80	1	16	5
Particles >38µm		ASTM D7647	>20	0	1	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	17/14/10	18/17/13	18/15/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974		0.042	0.029	0.039


Contact/Location: KEN TERRY - TALCLA




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		55.5	53.1	56.3
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					With a	
						A CONTRACTOR

Bottom





* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: KEN TERRY - TALCLA

T: (919)359-4362

F: (919)359-4767