

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area [1405005] Machine Id KAESER 1469 - ROECHLING Component

Compressor

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

			Feb2023	Feb2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06130762	UCH05813479	
Sample Date		Client Info		23 Feb 2024	14 Feb 2023	
Machine Age	hrs	Client Info		72933	67987	
Oil Age	hrs	Client Info		2308	22358	
Oil Changed		Client Info		Not Changd	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	0	
Chromium	ppm		>10	0	0 <1	
Nickel	ppm	ASTM D5185m	>3	1		
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	1	<1	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>50	19	19	
Tin	ppm	ASTM D5185m	>10	0	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	
Barium	ppm	ASTM D5185m	90	0	<1	
Molybdenum	ppm	ASTM D5185m	0	0	0	
Manganese	ppm	ASTM D5185m		0	<1	
Magnesium	ppm	ASTM D5185m	100	<1	3	
Calcium	ppm	ASTM D5185m	0	3	2	
Phosphorus	ppm	ASTM D5185m	0	4	16	
Zinc	ppm	ASTM D5185m	0	6	3	
Sulfur	ppm	ASTM D5185m	23500	22897	3351	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	
Sodium	ppm	ASTM D5185m		<1	<1	
Potassium	ppm	ASTM D5185m	>20	<1	<1	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.61	0.56	



OIL ANALYSIS REPORT

VISUAL



	White Metal	scalar	*Visual	NONE	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE	NONE		
	Debris	scalar	*Visual	NONE	MODER	HEAVY		
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE		
/24	Appearance	scalar	*Visual	NORML	NORML	NORML		
Feb 23/24	Odor	scalar	*Visual	NORML	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG	NEG		
	Free Water	scalar	*Visual	20.00	NEG	NEG		
				11 1. 1				
	FLUID PROPERT Visc @ 40°C	cSt	method ASTM D445	limit/base 45	current 48.5	history1 48.7	history2	
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2	
Feb23/24 +	Color						no image	
	Bottom					\bigcirc	no image	
	Ferrous Alloys	5		Feb23/24				
	Viscosity @ 40°C			Feb23/24	Acid Number			
	60 55 50 50 50 50 40 50 50 40 50 50 50 50 50 50 50 50 50 50 50 50 50			(D) H 0.91 (D) H 0.91 (D) H 0.077 (D) H 0.0777 (D) H 0.0777 (D) H 0.0777 (D) H 0.07777 (D) H 0.07777 (D) H 0.07777777 (D) H 0.07777777777777777777777777777777777	Basermal			
Laboratory Sample No. Lab Number Unique Number Test Package	: 10950227	Rece Teste	ived : 27 ed : 28	7, NC 27513 7 Mar 2024 8 Mar 2024 Mar 2024 - Dor		AIR TECHNOLOGIES INC (310 PLUM INDUSTRIAL PITTSBURGH ge US 15 Contact: MIKE STRAZZI		
discuss this sample report, Denotes test methods that tements of conformity to sp	contact Customer Servi are outside of the ISO 1	7025 scc	pe of accrea	litation.		trazzera@aircor T:		

Contact/Location: MIKE STRAZZERA - UCAIRPIT