

OIL ANALYSIS REPORT

Sample Rating Trend


DEGRADATION



Byron Center CAT 1 BYCM01BE

Biogas Engine

CHEVRON HDAX 9500 GAS ENGINE OIL 40 (--- GAL)





DIAGNOSIS

Recommendation

We recommend that you drain the oil and perform a filter service on this component if not already done. Resample at the next service interval to monitor. Please note that this is a corrected copy for diagnostic comment updates.

Wear

The tin level is abnormal. All other component wear rates are normal.

Contamination

Elemental level of silicon (Si) above normal.

▲ Fluid Condition

The BN level is low. The oil is no longer serviceable.

| S ENGINE OIL 40 (GAL) | | | | | | |
|------------------------|------------|-------------|------------|-------------|-------------|-------------|
| SAMPLE INFOR | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | WC0877088 | WC0877090 | WC0877092 |
| Sample Date | | Client Info | | 25 Mar 2024 | 15 Mar 2024 | 07 Mar 2024 |
| lachine Age | hrs | Client Info | | 86858 | 86629 | 86438 |
| Dil Age | hrs | Client Info | | 645 | 416 | 225 |
| il Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | SEVERE | NORMAL | NORMAL |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| uel | | WC Method | >4.0 | <1.0 | <1.0 | <1.0 |
| Vater | | WC Method | >0.11 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| on | ppm | ASTM D5185m | >15 | 6 | 2 | 2 |
| Chromium | ppm | ASTM D5185m | >4 | 0 | 0 | 0 |
| lickel | ppm | ASTM D5185m | | 0 | 0 | 0 |
| itanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| luminum | ppm | ASTM D5185m | >6 | 3 | 2 | 1 |
| .ead | ppm | ASTM D5185m | >9 | 0 | 1 | <1 |
| Copper | ppm | ASTM D5185m | >6 | 2 | 1 | <1 |
| in | ppm | ASTM D5185m | >4 | <u> </u> | 3 | 3 |
| anadium/ | ppm | ASTM D5185m | | 0 | 0 | 0 |
| admium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 2 | 3 | 2 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Nolybdenum | ppm | ASTM D5185m | | 2 | 1 | 2 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | <1 |
| /lagnesium | ppm | ASTM D5185m | | 31 | 19 | 21 |
| Calcium | ppm | ASTM D5185m | | 1901 | 1830 | 1676 |
| Phosphorus | ppm | ASTM D5185m | | 316 | 272 | 265 |
| Zinc Zinc | ppm | ASTM D5185m | | 388 | 319 | 318 |
| Sulfur | ppm | ASTM D5185m | | 3767 | 3549 | 3137 |
| CONTAMINANT | S | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >181 | 194 | 138 | 105 |
| Sodium | ppm | ASTM D5185m | >21 | <1 | 1 | <1 |
| otassium | ppm | ASTM D5185m | >20 | 2 | 0 | 0 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | | 0.1 | 0 | 0 |
| litration | Abs/cm | *ASTM D7624 | | 6.1 | 5.8 | 5.6 |
| Sulfation | Abs/.1mm | *ASTM D7415 | | 26.0 | 23.3 | 20.6 |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | | 17.3 | 14.6 | 12.1 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 1.0 | 2.08 | 1.57 | 1.18 |
| Page Number (DNI) | ma 1/011/a | ACTM DOOGS | E A | A 0.61 | 0.70 | 0.00 |

2.61


Base Number (BN) mg KOH/g ASTM D2896 5.4

2.79

3.33



OIL ANALYSIS REPORT







Certificate L2367

Sample No. Lab Number

Test Package : MOB 2

: WC0877088 : 06130795 Unique Number: 10950260

Tested Diagnosed

: 27 Mar 2024 : 28 Mar 2024

: 01 Apr 2024 - Doug Bogart

EDL NA Recips-Byron Center

Byron Center, MI US 49315

Contact: Jake Ripke

Jake.Ripke@edlenergy.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: