

OIL ANALYSIS REPORT

Area ULTRA FG [SVO-059806] Machine Id INGERSOLL RAND VL1992 - TERMINAL RAILROAD Component

Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		UCH06132135	UCH06088963		
Sample Date		Client Info		20 Mar 2024	01 Feb 2024		
Machine Age	hrs	Client Info		52396	51762		
Oil Age	hrs	Client Info		632	3378		
Oil Changed		Client Info		Not Changd	Changed		
Sample Status				NORMAL	ATTENTION		
CONTAMINATION	٧	method	limit/base	current	history1	history2	
Water		WC Method	>0.1	NEG	NEG		
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>50	0	<1		
Chromium	ppm	ASTM D5185m	>10	0	0		
Nickel	ppm	ASTM D5185m		0	0		
Titanium	ppm	ASTM D5185m		0	0		
Silver	ppm	ASTM D5185m		0	0		
Aluminum	ppm	ASTM D5185m	>25	0	0		
Lead	ppm	ASTM D5185m	>25	0	0		
Copper	ppm	ASTM D5185m	>50	0	0		
Tin	ppm	ASTM D5185m	>15	0	0		
Vanadium	ppm	ASTM D5185m		0	0		
Cadmium	ppm	ASTM D5185m		0	0		
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		0	0		
Barium	ppm	ASTM D5185m		1	1		
Molybdenum	ppm	ASTM D5185m		0	<1		
Manganese	ppm	ASTM D5185m		0	0		
Magnesium	ppm	ASTM D5185m		0	0		
Calcium	ppm	ASTM D5185m		55	47		
Phosphorus	ppm	ASTM D5185m		270	204		
Zinc	ppm	ASTM D5185m		0	<1		
Sulfur	ppm	ASTM D5185m		558	376		
CONTAMINANTS		method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	0	0		
Sodium	ppm	ASTM D5185m		12	9		
Potassium	ppm	ASTM D5185m	>20	0	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045		0.20	0.24		



OIL ANALYSIS REPORT

VISUAL





	VISUAL		method			history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
/24 -	Appearance	scalar	*Visual	NORML	NORML	NORML	
Mar20/24	Odor	scalar	*Visual	NORML	NORML	NORML	
_	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual	20.1	NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	46.0	53.4	57.2	
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Mar20/24 +	Color						no image
	Bottom						no image
	Ferrous Alloys			Mar20/24			
	Non-ferrous Metal	S		Mar2024			
	Viscosity @ 40°C				Acid Numbe	r	
	60 Abnormal			Mar20/24 Acid Number (mg KOH/g) 10 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0	10		
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report	: UCH06132135 : 06132135 : 10951600 : IND 2 ; contact Customer Serv.	n Ave., Cary, NC 27513 ved : 28 Mar 2024 d : 29 Mar 2024 iosed : 02 Apr 2024 - Jonathan Hester			JOHN HENRY FOSTER COMPAN 4700 LEBOURGET STREE SAINT LOUIS, M US 6313 Contact: RACHEL VON HATTE rvonhatten@jhf.cor T: (314)593-126		

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: RACHEL VON HATTEN - UCJOHSAI

F: (314)874-0965