# OIL ANALYSIS REPORT

Sample Rating Trend




NORMAL

Machine Id
## FRICK 7022 - BC 7 RDB 546 (S/N 50011GFMTHAA3)
Component
**Refrigeration Compressor**
Fluid
**USPI 1009-68 SC (250 GAL)**

## DIAGNOSIS

**Recommendation**
Resample at the next service interval to monitor.

**Wear**
All component wear rates are normal.

**Contamination**
There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

**Fluid Condition**
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Sample Number | | Client Info | | **USP0008291** | USP0004514 | USP250164 |
| Sample Date | | Client Info | | **20 Mar 2024** | 21 Dec 2023 | 15 Jun 2023 |
| Machine Age | hrs | Client Info | | **91888** | 89692 | 85329 |
| Oil Age | hrs | Client Info | | **0** | 0 | 0 |
| Oil Changed | | Client Info | | **N/A** | N/A | N/A |
| Sample Status | | | | **NORMAL** | NORMAL | NORMAL |

| WEAR METALS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Iron | ppm | ASTM D5185m | >8 | **0** | 0 | 1 |
| Chromium | ppm | ASTM D5185m | >2 | **<1** | 0 | 0 |
| Nickel | ppm | ASTM D5185m | | **<1** | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Silver | ppm | ASTM D5185m | >2 | **0** | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >3 | **<1** | 0 | 0 |
| Lead | ppm | ASTM D5185m | >2 | **0** | 0 | 0 |
| Copper | ppm | ASTM D5185m | >8 | **0** | <1 | 0 |
| Tin | ppm | ASTM D5185m | >4 | **0** | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | **0** | 0 | 0 |

| ADDITIVES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Boron | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Barium | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | **0** | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | | **0** | <1 | 0 |
| Calcium | ppm | ASTM D5185m | | **0** | 1 | 0 |
| Phosphorus | ppm | ASTM D5185m | | **0** | <1 | 0 |
| Zinc | ppm | ASTM D5185m | | **0** | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 50 | **0** | 69 | 61 |

| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Silicon | ppm | ASTM D5185m | >15 | **0** | <1 | 0 |
| Sodium | ppm | ASTM D5185m | | **<1** | 1 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | **<1** | 0 | 0 |
| Water | % | ASTM D6304 | >0.01 | **0.003** | 0.002 | 0.003 |
| ppm Water | ppm | ASTM D6304 | >100 | **33** | 24 | 35.7 |

| FLUID CLEANLINESS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Particles >4µm | | ASTM D7647 | | **3987** | 2901 | 8094 |
| Particles >6µm | | ASTM D7647 | >2500 | **483** | 476 | 1596 |
| Particles >14µm | | ASTM D7647 | >320 | **17** | 18 | 45 |
| Particles >21µm | | ASTM D7647 | >80 | **4** | 5 | 7 |
| Particles >38µm | | ASTM D7647 | >20 | **0** | 0 | 0 |
| Particles >71µm | | ASTM D7647 | >4 | **0** | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >--/18/15 | **19/16/11** | 19/16/11 | 20/18/13 |

| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Acid Number (AN) | mg KOH/g | ASTM D974 | 0.005 | **0.028** | 0.014 | 0.015 |

# OIL ANALYSIS REPORT

Water (KF)




Particle Trend




Water (KF)




Viscosity @ 40°C




Particle Trend




| VISUAL | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| White Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Silt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Debris | scalar | *Visual | NONE | **NONE** | NONE | LIGHT |
| Sand/Dirt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Appearance | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Odor | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.01 | **NEG** | NEG | NEG |
| Free Water | scalar | *Visual | | **NEG** | NEG | NEG |

| FLUID PROPERTIES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Visc @ 40°C | cSt | ASTM D445 | 67 | **74.6** | 73.1 | 73.6 |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|
| Color | | |  | | |
| Bottom | | |  | | |

## GRAPHS

Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C




Particle Count




Acid Number




**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513
**Sample No.** : USP0008291
**Lab Number** : 06133436
**Unique Number** : 10952901
**Test Package** : IND 2

**Received** : 29 Mar 2024
**Tested** : 01 Apr 2024
**Diagnosed** : 01 Apr 2024 - Doug Bogart

Certificate L2367

*To discuss this sample report, contact Customer Service at 1-800-237-1369.*
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
*Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)*

**BLUE BELL-SYLACAUGA**
423 NORTH NORTON
SYLACAUGA, AL
US 35150
Contact: FAYE TAYLOR
faye.taylor@bluebell.com
T: (256)249-6100
F: (256)249-6197