

OIL ANALYSIS REPORT

Sample Rating Trend





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

			2022	Jul2023 Feb20	124	
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0832069	WC0832073	WC0699803
Sample Date		Client Info		13 Feb 2024	05 Jul 2023	13 Oct 2022
Machine Age	mls	Client Info		237697	141552	40564
Oil Age	mls	Client Info		237697	50000	40564
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	1	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	37	49	70
Chromium	ppm	ASTM D5185m	>20	<1	<1	1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>20	6	9	42
Lead	ppm	ASTM D5185m	>40	0	0	3
Copper	ppm	ASTM D5185m	>330	2	7	20
Tin	ppm	ASTM D5185m	>15	<1	<1	2
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	0.00	AOTH DEADE		-		0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ррп	method	limit/base	0 current	0 history1	0 history2
	ppm		limit/base 250	-	-	-
ADDITIVES		method		current	history1	history2
ADDITIVES Boron	ppm	method ASTM D5185m	250	current 7	history1 18	history2 21
ADDITIVES Boron Barium	ppm ppm	method ASTM D5185m ASTM D5185m	250 10	current 7 0	history1 18 0	history2 21 0
ADDITIVES Boron Barium Molybdenum	ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m	250 10	current 7 0 73	history1 18 0 71	history2 21 0 22
ADDITIVES Boron Barium Molybdenum Manganese	ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	250 10 100	current 7 0 73 <1	history1 18 0 71 1	history2 21 0 22 2
ADDITIVES Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	250 10 100 450	current 7 0 73 <1 951	history1 18 0 71 1 913	history2 21 0 22 2 2 753
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	250 10 100 450 3000	Current 7 0 73 <1 951 1375	history1 18 0 71 1 913 1335	history2 21 0 22 2 2 753 1604
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	250 10 100 450 3000 1150	Current 7 0 73 <1 951 1375 1090	history1 18 0 71 1 913 1335 1065	history2 21 0 22 2 753 1604 787
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350	Current 7 0 73 <1 951 1375 1090 1332	history1 18 0 71 1 913 1335 1065 1305	history2 21 0 22 2 753 1604 787 1055
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250	Current 7 0 73 <1 951 1375 1090 1332 3590	history1 18 0 71 1 913 1335 1065 1305 3478	history2 21 0 22 23 1604 787 1055 3640
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS	ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	250 10 100 450 3000 1150 1350 4250	Current 7 0 73 <1 951 1375 1090 1332 3590 Current	history1 18 0 71 1 913 1335 1065 1305 3478 history1	history2 21 0 22 2 753 1604 787 1055 3640 history2
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon	ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250	current 7 0 73 <1 951 1375 1090 1332 3590 current 14	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16	history2 21 0 22 2 753 1604 787 1055 3640 history2 12
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium	ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250 limit/base >25	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4	history2 21 0 22 23 1604 787 1055 3640 history2 12 4
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium	ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250 limit/base >25 >20	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2 8	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4 15	history2 21 0 22 23 753 1604 787 1055 3640 history2 12 4 104
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED	ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250 Imit/base >25 >20	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2 8 current	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4 15 history1	history2 21 0 22 2 753 1604 787 1055 3640 history2 12 4 104 history2
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250 limit/base >25 >20 limit/base	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2 8 current 0.6	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4 15 history1 0.5	history2 21 0 22 753 1604 787 1055 3640 history2 12 4 104 history2 0 3630
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m	250 10 100 450 3000 1150 1350 4250 imit/base >25 >20 imit/base >3 >20	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2 8 current 0.6 13.2	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4 15 history1 0.5 13.3	history2 21 0 22 753 1604 787 1055 3640 history2 12 4 104 history2 0.3 12.1
ADDITIVES Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	method ASTM D5185m ASTM D5185m	250 10 100 450 3000 1150 1350 4250 imit/base >25 imit/base >3 >20 >30	current 7 0 73 <1 951 1375 1090 1332 3590 current 14 2 8 current 0.6 13.2 26.5	history1 18 0 71 1 913 1335 1065 1305 3478 history1 16 4 15 history1 0.5 13.3 26.1	history2 21 0 22 2 753 1604 787 1055 3640 history2 12 4 104 history2 0.3 12.1 25.7





OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	10.9	11.9	11.7	12.5
GRAPHS						
Ferrous Alloys						





Ē

Contact/Location: GARY LAWYER - MIDWIL

F: