

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

Westchester des fleet#577620 G13b086016

Component

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		Mar202	1 May2022	May2023 N	ar2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0921717	WC0799923	WC0651427
Sample Date		Client Info		21 Mar 2024	11 May 2023	09 May 2022
Machine Age	hrs	Client Info		233	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	٧	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	0	<1	1
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	<1	<1	<1
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	0	0	<1
Tin	ppm	ASTM D5185m	>15	0	<1	0
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	4	14	4
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	62	48	56
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	450	1017	641	811
Calcium	ppm	ASTM D5185m	3000	1206	1542	1098
Phosphorus	ppm	ASTM D5185m	1150	1073	1046	955
Zinc	ppm	ASTM D5185m	1350	1281	1293	1169
Sulfur	ppm	ASTM D5185m	4250	4267	4002	3181
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	5	5
Sodium	ppm	ASTM D5185m	>158	0	1	<1
Potassium	ppm	ASTM D5185m	>20	2	6	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	4.5	4.3	4.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.9	16.2	17.3
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.8	11.7	12.6
Oxidation Base Number (BN)	Abs/.1mm mg KOH/g	*ASTM D7414 ASTM D2896	>25 8.5	12.8 9.7	11.7 8.8	12.6 9.4



OIL ANALYSIS REPORT





GRAPH	S						
Iron (pp	m)			Lead (pp	om)		
200 Severe				Severe			
150 - Abnormal				Abnormal			
100 Abnormal				Abnormal			
50				20			
Mar25/21-	May9/22 -	May11/23 -	Mar21/24	Mar25/21-	May9/22 -	May11/23 -	Mar21/24
		May	Mar	_		May	Mar
Aluminui	m (ppm)			Chromiu 50 T	m (ppm)		
40 - Severe				40 - Severe		·	
Abnormal				Abnormal			
10				10			
0	2	22	4	0	2		
Mar25/21	May9/22	May11/23	Mar21/24	Mar25/2	May9/22	May11/23	Mar21/24
Copper ((ppm)	2	2	Silicon (p		2	_
400 Severe				80 - Severe		!	
300				60-			
E 200				Abnormal			
100				20			
5/211	May9/22	1/23	1/24	0 12/2/2	May9/22 -	1/23	1/24
Mar25/21		May11/23	Mar21/24	Mar25/21	Мау	May11/23	Mar21/24
Viscosity	@ 100°C			Base Nu	mber		
Abnormal				Abnormal Abnormal Abnormal		: :	
Base Abnormal	***************************************			Base			
Abnormal				5.0 - Abnormal		1 1 1	
10				0.0			
Mar25/21	May9/22	May11/23	Mar21/24	Mar25/21	May9/22	May11/23.	Mar21/24 -
Ž	Σ	Mai	Ma	M	≥	Mar	ĕ



Laboratory Sample No.

Lab Number : 06134610 **Unique Number** : 10954075

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0921717 Received : 01 Apr 2024

Tested Diagnosed

: 02 Apr 2024

: 02 Apr 2024 - Wes Davis Test Package : MOB 1 (Additional Tests: TBN)

US 12553 Contact: JOE SAYEGH joe@gentechltd.com T: (845)568-0500

GEN TECH LTD

NEW WINDSOR, NY

3017 RT 9W

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (845)568-3073

Contact/Location: JOE SAYEGH - GENNEW