


OIL ANALYSIS REPORT

Sample Rating Trend

SAMPLE INFORMATION method limit/base





BUSCH VP-8C (S/N U045205618)

Vacuum Pump Fluid USPI VAC 100 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM		method	limit/base	current	nistory i	nistory2
Sample Number		Client Info		USPM36580	USPM30545	USPM29769
Sample Date		Client Info		31 Mar 2024	07 Jan 2024	23 Sep 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	ABNORMAL
		and the set	11.0011/000000		Istatement	h is have a
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	<1	0
Chromium	ppm	ASTM D5185m	>20	<1	<1	0
Nickel	ppm	ASTM D5185m	>20	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	2	3
Lead	ppm	ASTM D5185m	>20	0	<1	0
Copper	ppm		>20	0	<1	<1
Tin	ppm	ASTM D5185m	>20	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	<1	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	<1	0
Manganese	ppm	ASTM D5185m	Ū	<1	<1	<1
Magnesium	ppm	ASTM D5185m	0	0	<1	<1
Calcium	ppm	ASTM D5185m		<1	<1	<1
Phosphorus	ppm	ASTM D5185m	1800	822	1059	398
Zinc	ppm	ASTM D5185m	0	0	0	0
Sulfur	ppm	ASTM D5185m	0	10	0	59
CONTAMINANTS	:	method	limit/base	current	history1	history2
Silicon				2	4	
Sodium	ppm ppm	ASTM D5185m ASTM D5185m	>15	2	0	9
Potassium		ASTM D5185m	>20	۰ <1	<1	2
Water	ppm %	ASTM D5105III		0.048	▲ 0.117	0.494
ppm Water	ppm	ASTM D0304 ASTM D6304		484	▲ 1171	▲ 4940
		AS THE DOUG		-0-		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	4195	🔺 13961	2404
Particles >6µm		ASTM D7647	>1300	1219	<mark>▲</mark> 3273	625
Particles >14µm		ASTM D7647	>160	91	A 200	14
Particles >21µm		ASTM D7647		20	<u> </u>	3
Particles >38µm		ASTM D7647		0	2	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/17/14	🔺 21/19/15	18/16/11
FLUID DEGRADA	ATION _	method	limit/base	current	history1	history2
Acid Number (AN)	ma KOH/a	ASTM D8045	0.05	0.066	0.089	0.18
	iiiy NO⊓/ÿ	AG HVI DOU40	0.00	0.000	0.009	0.10


Contact/Location: SERVICE MANAGER ? - TYSAMAPRO




OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.1	NEG	NEG	0.2%
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
FLUID PROPERT Visc @ 40°C	TES cSt	method ASTM D445	limit/base 91	current 97.7	history1 91.8	history2 81.3
	cSt					
Visc @ 40°C	cSt	ASTM D445	91	97.7	91.8	81.3



Contact/Location: SERVICE MANAGER ? - TYSAMAPRO