




# OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id  
**C-2702A EAST (S/N MK6C/WRV1321132/58/743)**

Component  
**Refrigeration Compressor**  
Fluid  
**USPI ALT-68 SC (210 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>USP247266</b>	USP0006197	USP0003722
Sample Date	Client Info		<b>29 Mar 2024</b>	17 Mar 2024	07 Nov 2023
Machine Age	hrs	Client Info	<b>0</b>	0	0
Oil Age	hrs	Client Info	<b>0</b>	2	0
Oil Changed	Client Info		<b>N/A</b>	N/A	N/A
Sample Status			<b>ABNORMAL</b>	ABNORMAL	ABNORMAL

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >8	<b>&lt;1</b>	4	3
Chromium	ppm	ASTM D5185m >2	<b>&lt;1</b>	0	0
Nickel	ppm	ASTM D5185m	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m	<b>0</b>	0	0
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >3	<b>0</b>	0	0
Lead	ppm	ASTM D5185m >2	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m >8	<b>0</b>	0	<1
Tin	ppm	ASTM D5185m >4	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m	<b>0</b>	<1	<1
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	<b>0</b>	0	0
Barium	ppm	ASTM D5185m	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	<b>0</b>	0	0
Manganese	ppm	ASTM D5185m	<b>&lt;1</b>	0	<1
Magnesium	ppm	ASTM D5185m	<b>0</b>	0	0
Calcium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0
Phosphorus	ppm	ASTM D5185m	<b>0</b>	0	<1
Zinc	ppm	ASTM D5185m	<b>2</b>	<1	5
Sulfur	ppm	ASTM D5185m 50	<b>16</b>	0	22

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	<b>&lt;1</b>	<1	4
Sodium	ppm	ASTM D5185m	<b>0</b>	<1	<1
Potassium	ppm	ASTM D5185m >20	<b>0</b>	0	<1
Water	%	ASTM D6304 >0.01	<b>0.003</b>	0.007	0.005
ppm Water	ppm	ASTM D6304 >100	<b>34</b>	71	55.0

## FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>10000	<b>▲ 51723</b>	---	▲ 161016
Particles >6µm	ASTM D7647	>2500	<b>▲ 7900</b>	---	▲ 67783
Particles >14µm	ASTM D7647	>320	<b>161</b>	---	▲ 4070
Particles >21µm	ASTM D7647	>80	<b>20</b>	---	▲ 673
Particles >38µm	ASTM D7647	>20	<b>0</b>	---	6
Particles >71µm	ASTM D7647	>4	<b>0</b>	---	0
Oil Cleanliness	ISO 4406 (c)	>20/18/15	<b>▲ 23/20/15</b>	---	▲ 25/23/19


## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974 0.005	<b>0.014</b>	0.042	0.013




# OIL ANALYSIS REPORT


## Particle Trend




## Water (KF)




## Acid Number



## Water (KF)




## Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	▲ MODER	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	65.6	61.6	62.2

## SAMPLE IMAGES




## GRAPHS


### Ferrous Alloys




### Non-ferrous Metals




### Viscosity @ 40°C



### Particle Count



### Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
 Sample No. : USP247266  
 Lab Number : 06135028  
 Unique Number : 10954493  
 Test Package : IND 2  
 Received : 01 Apr 2024  
 Tested : 02 Apr 2024  
 Diagnosed : 02 Apr 2024 - Doug Bogart

**REC SILICON MATERIALS**  
 119140 RICK JONES WAY  
 SILVER BOW, MT  
 US 59750  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: