

## **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id **ARIEL AGI 9100** Reciprocating Compressor Fluid TULCO (20 GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Feb2023	Apr2023 Jun2023	Sep2023 Nov2023 Jan2024	Mar2024	
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		TO60000612	TO60000615	TO60000644
Sample Date		Client Info		26 Mar 2024	21 Feb 2024	26 Jan 2024
Machine Age	hrs	Client Info		50387	50387	50332
Oil Age	hrs	Client Info		0	16000	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	0
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m		0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	<1	0
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m		9	<1	<1
Tin	ppm	ASTM D5185m	>15	ر 1	<1	0
Vanadium	ppm	ASTM D5185m	210	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ррш		limit/base	-	-	-
		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		2	3	<1
Calcium	ppm	ASTM D5185m		5	0	3
Phosphorus	ppm	ASTM D5185m		71	66	63
Zinc	ppm	ASTM D5185m		9	5	1
Sulfur	ppm	ASTM D5185m		997	900	926
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	0
Sodium	ppm	ASTM D5185m		0	0	<1
Potassium	ppm	ASTM D5185m	>20	<1	<1	0
Water	%	ASTM D6304	>0.1	0.005	0.003	0.007
ppm Water	ppm	ASTM D6304	>1000	55	38	76
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>1300	936	<b>A</b> 2739	734
Particles >6µm		ASTM D7647	>640	151	443	100
Particles >14µm		ASTM D7647	>160	22	13	3
Particles >21µm		ASTM D7647	>40	7	1	1
Particles >38µm		ASTM D7647	>10	0	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>17/16/14	17/14/12	▲ 19/16/11	17/14/9
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.07	0.105	0.079


Contact/Location: Service Manager - CFSPEA Page 1 of 2



# **OIL ANALYSIS REPORT**








80

CILCU

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		143	151	146
Visc @ 100°C	cSt	ASTM D445		16.9	17.4	17.0
Viscosity Index (VI)	Scale	ASTM D2270		127	125	126
SAMPLE IMAGES	;	method	limit/base	current	history1	history2
Color				•		
					1/45	

Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: Service Manager - CFSPEA Page 2 of 2