<u>Sullivan</u> Palatek

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area NOT GIVEN Machine Id SULLIVAN PALATEK 21JE002535

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination


There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCS06135075	UCS06018278	
Sample Date		Client Info		11 Mar 2024	26 Nov 2023	
Machine Age	hrs	Client Info		13990	0	
Oil Age	hrs	Client Info		4805	0	
Oil Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	
Chromium	ppm	ASTM D5185m	>10	0	<1	
Nickel	ppm	ASTM D5185m		0	<1	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	<1	
Lead	ppm	ASTM D5185m	>25	0	<1	
Copper	ppm	ASTM D5185m	>50	<1	2	
Tin	ppm	ASTM D5185m	>15	0	<1	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		0	11	
Molybdenum	ppm	ASTM D5185m		0	<1	
Manganese	ppm	ASTM D5185m		0	<1	
Magnesium	ppm	ASTM D5185m		0	<1	
Calcium	ppm	ASTM D5185m		1	0	
Phosphorus	ppm	ASTM D5185m		64	539	
Zinc	ppm	ASTM D5185m		124	0	
Sulfur	ppm	ASTM D5185m		12	1183	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	2	
Sodium	ppm	ASTM D5185m		4	0	
Potassium	ppm	ASTM D5185m	>20	0	<1	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.541	0.09	

OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Marl 1/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Mar	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		61.26	46.5	
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Mari 1/24	Color						no image
	Bottom						no image
	Ferrous Alloys	s		Mart 1/24			
	Viscosity @ 40°C		entiteseet)	Mat1124	Acid Number		
	65 60				°T :		
				Q 0.4	8		
	C 555 € 50 ₹ 45			0.6() (0) (0) (0) (0) (0) (0) (0) (0) (0)	4		
	45 - Abnormal			2 0 1			
	35						
	Nav26/23			Mar11/24	Nov26/23		
	Novi			Mar	Nov		
B Sample No.	: WearCheck USA - 50 : UCS06135075 : 06135075	1 Madiso Recei Teste	ved : 01	r, NC 27513 Apr 2024 5 Apr 2024	ALL AN	MERICAN AIR CC	OMPRESSOR

Report Id: UCALLVAN [WUSCAR] 06135075 (Generated: 04/08/2024 09:05:31) Rev: 1

Contact/Location: PARTS ? - UCALLVAN