


# **OIL ANALYSIS REPORT**

ENGINE ROOM C-6 (S/N 10242F05813036)

Refrigeration Compressor

FRICK COMPRESSOR OIL #3 (65 GAL)



Sample Rating Trend



## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

## **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM    | MATION   | method       | limit/base | current     | history1    | history2    |
|------------------|----------|--------------|------------|-------------|-------------|-------------|
| Sample Number    |          | Client Info  |            | USP0008163  | USP0005203  | USP243639   |
| Sample Date      |          | Client Info  |            | 28 Mar 2024 | 27 Dec 2023 | 09 Oct 2023 |
| Machine Age      | hrs      | Client Info  |            | 1158        | 10743       | 10140       |
| Oil Age          | hrs      | Client Info  |            | 0           | 10743       | 10140       |
| Oil Changed      |          | Client Info  |            | N/A         | N/A         | N/A         |
| Sample Status    |          |              |            | NORMAL      | NORMAL      | NORMAL      |
| WEAR METALS      |          | method       | limit/base | current     | history1    | history2    |
| Iron             | ppm      | ASTM D5185m  | >8         | <1          | 0           | 0           |
| Chromium         | ppm      | ASTM D5185m  | >2         | <1          | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m  |            | <1          | 0           | <1          |
| Titanium         | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Silver           | ppm      | ASTM D5185m  | >2         | 0           | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m  | >3         | 0           | 0           | 0           |
| Lead             | ppm      | ASTM D5185m  | >2         | <1          | 0           | <1          |
| Copper           | ppm      | ASTM D5185m  | >8         | <1          | 0           | 0           |
| Tin              | ppm      | ASTM D5185m  | >4         | 1           | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| ADDITIVES        |          | method       | limit/base | current     | history1    | history2    |
| Boron            | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Barium           | ppm      | ASTM D5185m  |            | 0           | 0           | 3           |
| Molybdenum       | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Magnesium        | ppm      | ASTM D5185m  |            | <1          | 0           | <1          |
| Calcium          | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Phosphorus       | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Zinc             | ppm      | ASTM D5185m  |            | 0           | 0           | <1          |
| Sulfur           | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| CONTAMINANTS     |          | method       | limit/base | current     | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m  | >15        | 1           | 0           | <1          |
| Sodium           | ppm      | ASTM D5185m  | 7.0        | 0           | 0           | 0           |
| Potassium        | ppm      | ASTM D5185m  | >20        | 1           | 0           | <1          |
| Water            | %        | ASTM D6304   | >0.01      | 0.001       | 0.002       | 0.001       |
| ppm Water        | ppm      | ASTM D6304   | >100       | 14          | 24          | 13.5        |
| FLUID CLEANLIN   | IESS     | method       | limit/base | current     | history1    | history2    |
| Particles >4µm   |          | ASTM D7647   | >10000     | 3906        | 1514        | 617         |
| Particles >6µm   |          | ASTM D7647   | >2500      | 650         | 290         | 156         |
| Particles >14µm  |          | ASTM D7647   | >320       | 26          | 16          | 7           |
| Particles >21µm  |          | ASTM D7647   | >80        | 4           | 4           | 2           |
| Particles >38µm  |          | ASTM D7647   | >20        | 0           | 0           | 0           |
| Particles >71µm  |          | ASTM D7647   | >4         | 0           | 0           | 0           |
| Oil Cleanliness  |          | ISO 4406 (c) | >20/18/15  | 19/17/12    | 18/15/11    | 16/14/10    |
| FLUID DEGRADA    | TION     | method       | limit/base | current     | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D974    |            | 0.013       | 0.013       | 0.015       |



# **OIL ANALYSIS REPORT**







Certificate 12367

Laboratory Sample No.

: USP0008163 Lab Number : 06135712

Unique Number : 10955177 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 01 Apr 2024

**Tested** : 04 Apr 2024

Diagnosed : 04 Apr 2024 - Doug Bogart **TYSON - ROCHELLE** 

ROCHELLE, IL US 61068

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: TYSROC [WUSCAR] 06135712 (Generated: 04/05/2024 20:12:54) Rev: 1

Contact/Location: Service Manager - TYSROC

T:

F: