

## **OIL ANALYSIS REPORT**

Sample Number

hrs

hrs

Sample Date

Machine Age

Oil Changed

Sample Status

CONTAMINATION

Oil Age

Fuel

Water

### CLAY DUNIGAN JOHN DEERE 1025R 1LV1025RENP859212 Component

**Diesel Engine** 

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- QTS)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

Metal levels are typical for a new component breaking in.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>51	7		
Chromium	ppm	ASTM D5185m	>11	<1		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>31	4		
Lead	ppm	ASTM D5185m	>26	0		
Copper	ppm	ASTM D5185m	>26	2		
Tin	ppm	ASTM D5185m	>4	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		308		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		255		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		786		
Calcium	ppm	ASTM D5185m		1510		
Phosphorus	ppm	ASTM D5185m		937		
Zinc	ppm	ASTM D5185m		1091		
Sulfur	ppm	ASTM D5185m		3511		
CONTAMINAN	ſS	method	limit/base	current	history1	history2

CONTAININA		methou	iiiiii/base	Current	Thistory I	mstoryz
Silicon	ppm	ASTM D5185m	>22	36		
Sodium	ppm	ASTM D5185m	>31	6		
Potassium	maa	ASTM D5185m	>20	3		

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1		
Nitration	Abs/cm	*ASTM D7624	>20	6.7		
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.2		
FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3		
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.8		



Abnorma

Ba

cSt (100°C)

13

12 Mar25/3

# **OIL ANALYSIS REPORT**

scalar

scalar

scalar

scalar

White Metal

Yellow Metal

Precipitate

Silt

Debris

\*Visual


\*Visual


\*Visual

\*Visual

scalar \*Visual

NONE





Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: COY STANLEY - QUASMI

F: