OIL ANALYSIS REPORT

Sample Rating Trend



ISO

Area
DICK LAVY
Machine Id
DICK LAVY 4851
Component
Rear Differential
Fluid
GEAR OIL SAE 75W90 (--- GAL)

DIAGNOSIS

Recommendation
We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is a high amount of particulates present in the oil.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0900819**	WC0853965	WC0815576
Sample Date		Client Info		**03 Mar 2024**	20 Oct 2023	17 May 2023
Machine Age	mls	Client Info		**318589**	256690	190226
Oil Age	mls	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**ABNORMAL**	ABNORMAL	ABNORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**213**	214	171
Chromium	ppm	ASTM D5185m	>10	**2**	2	1
Nickel	ppm	ASTM D5185m	>10	**0**	<1	0
Titanium	ppm	ASTM D5185m		**<1**	<1	<1
Silver	ppm	ASTM D5185m		**1**	0	0
Aluminum	ppm	ASTM D5185m	>25	**3**	2	<1
Lead	ppm	ASTM D5185m	>25	**0**	0	0
Copper	ppm	ASTM D5185m	>100	**2**	2	2
Tin	ppm	ASTM D5185m	>10	**<1**	<1	0
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**<1**	<1	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	**157**	170	136
Barium	ppm	ASTM D5185m	200	**3**	0	0
Molybdenum	ppm	ASTM D5185m	12	**<1**	1	<1
Manganese	ppm	ASTM D5185m		**17**	18	15
Magnesium	ppm	ASTM D5185m	12	**10**	8	8
Calcium	ppm	ASTM D5185m	150	**26**	23	24
Phosphorus	ppm	ASTM D5185m	1650	**1044**	1075	1113
Zinc	ppm	ASTM D5185m	125	**36**	19	24
Sulfur	ppm	ASTM D5185m	22500	**24724**	27630	29466

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	**33**	39	23
Sodium	ppm	ASTM D5185m		**6**	4	4
Potassium	ppm	ASTM D5185m	>20	**5**	4	3
Water	%	ASTM D6304	>.2	**0.030**	0.027	0.025
ppm Water	ppm	ASTM D6304	>2000	**306**	273	257.8

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	▲ **107779**	▲ 77006	▲ 53132
Particles >6µm		ASTM D7647	>5000	▲ **27777**	4605	1919
Particles >14µm		ASTM D7647	>640	▲ **897**	20	18
Particles >21µm		ASTM D7647	>160	▲ **168**	3	4
Particles >38µm		ASTM D7647	>40	**3**	0	0
Particles >71µm		ASTM D7647	>10	**0**	0	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	▲ **24/22/17**	▲ 23/19/11	▲ 23/18/11

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	2.00	**2.95**	2.51	2.69

OIL ANALYSIS REPORT

Particle Trend



Water (KF)



Viscosity @ 100°C



Water (KF)



Viscosity @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	109	**96.8**	96.2	96.3
Visc @ 100°C	cSt	ASTM D445	16.0	**14.4**	14.5	14.5
Viscosity Index (VI)	Scale	ASTM D2270	157	**153**	156	156

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0900819 **Received** : 02 Apr 2024
Lab Number : 06136374 **Tested** : 03 Apr 2024
Unique Number : 10955839 **Diagnosed** : 04 Apr 2024 - Don Baldridge
Test Package : MOB 2 (Additional Tests: KF, KV100, PrtCount, VI)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

BASF - GIANNA CREDAROLI
500 WHITE PLAINS RD
TARRYTOWN, NY
US 10591
Contact: GIANNA CREDAROLI
gianna.credaroli@basf.com
T:
F: