

OIL ANALYSIS REPORT

_





VOLVO A25D 742205

Component
Rear Axle

VOLVO PREMIUM GEAR OIL 80W-90 GL-5 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

JIL 80W-90 GL-5 (- GAL)			Mar2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0000457		
Sample Date		Client Info		26 Mar 2024		
Machine Age	hrs	Client Info		4305		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>900	291		
Chromium	ppm	ASTM D5185m	>20	6		
Nickel	ppm	ASTM D5185m	>10	4		
Гitanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	<1		
_ead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m	>150	17		
Fin	ppm	ASTM D5185m	>20	1		
/anadium	ppm	ASTM D5185m	720	<1		
Cadmium	ppm	ASTM D5185m		0		
	РРШ		limit/bass			
ADDITIVES		method	limit/base		history1	history2
Boron	ppm	ASTM D5185m	379	198		
Barium	ppm	ASTM D5185m	0.0	0		
Molybdenum	ppm	ASTM D5185m	8.0	4		
Manganese	ppm	ASTM D5185m	0.0	9		
Magnesium	ppm	ASTM D5185m	31	0		
Calcium	ppm	ASTM D5185m	38	31		
Phosphorus	ppm	ASTM D5185m	1077	1065		
Zinc	ppm	ASTM D5185m	46	4		
Sulfur	ppm	ASTM D5185m	23526	30669		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	5		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
ellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
20.54) Day: 1	Journal	Vioudi	Cor		OMMV CDIEEIN	VOLVOOSE




OIL ANALYSIS REPORT





FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	139	114		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						

Ferrous Alloys



Non-ferrous Metals







Certificate 12367

Laboratory

Sample No. : ML0000457 Lab Number : 06136987 $\textbf{Unique Number} \quad : 10956452$

Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 02 Apr 2024

Tested : 03 Apr 2024

Diagnosed : 05 Apr 2024 - Sean Felton

MCCLUNG-LOGAN EQUIPMENT CO - CHESAPEAKE 4112 HOLLAND BLVD CHESAPEAKE, VA US 23323

Contact: TOMMY GRIFFIN tgriffin@mcclung-logan.com T: (757)485-3314

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (757)485-3415