

OIL ANALYSIS REPORT





Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


NORWAL


.....


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ST46530	ST46192	ST43890
Sample Date		Client Info		02 Apr 2024	21 Dec 2023	28 Sep 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	10	<1	2
Chromium	ppm	ASTM D5185m	>15	<1	0	0
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	0	0
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>200	0	0	0
Tin	ppm	ASTM D5185m	>25	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	0	1	<1
Barium	ppm	ASTM D5185m	15	0	0	0
Molybdenum	ppm	ASTM D5185m	15	0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	50	<1	0	<1
Calcium	ppm	ASTM D5185m	50	5	0	<1
Phosphorus	ppm	ASTM D5185m	350	371	336	303
Zinc	ppm	ASTM D5185m	100	3	0	2
Sulfur	ppm	ASTM D5185m	12500	20327	17345	17583
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	15	15	16
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	2	0	<1
Water	%	ASTM D6304	>0.2	0.001	0.006	0.003
ppm Water	ppm	ASTM D6304	>2000	14	69	38.3
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>40000	15561	12422	6508
Particles >6µm		ASTM D7647	>5000	2346	1600	757
Particles >14µm		ASTM D7647	>640	113	70	19
Particles >21µm		ASTM D7647	>160	29	19	4
Particles >38µm		ASTM D7647	>40	2	2	1
Particles >71µm		ASTM D7647	>10	1	0	1
Oil Cleanliness		ISO 4406 (c)	>22/19/16	21/18/14	21/18/13	20/17/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	1.27	1.18	1.14




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	212	211	211
SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Color				a.		

Bottom



Diagnosed



: 04 Apr 2024 DARTMOUTH, MA : 05 Apr 2024 - Don Baldridge US 02745 Test Package : IND 2 (Additional Tests: KF, PrtCount) Contact: Greg Walton To discuss this sample report, contact Customer Service at 1-800-237-1369. greg.walton@zapp.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. F: (508)998-6310 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: ZAPDAR [WUSCAR] 06137424 (Generated: 04/05/2024 18:06:28) Rev: 1

Certificate 12367

Laboratory

Sample No.

Unique Number : 10956889

Contact/Location: Greg Walton - ZAPDAR Page 2 of 2

T: