

# **OIL ANALYSIS REPORT**

Sample Rating Trend

**WEAR** 



Machine Id CATERPILLAR 745D 1340 **Rear Differential** 

Fluid {not provided} (--- GAL)

## DIAGNOSIS

#### Recommendation

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

### 🔺 Wear

The copper level is abnormal. All other component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The condition of the oil is acceptable for the time in service.

3407 (S/N 3T60	6505)					
	10000)					
				Apr2024		
SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0913158		
Sample Date		Client Info		01 Apr 2024		
Machine Age	hrs	Client Info		2290		
Dil Age Dil Changed	hrs	Client Info Client Info		2290 Changed		
Sample Status		Client Inio		ABNORMAL		
		method	limit/base	current	history1	history2
Vater	v	WC Method	>.2	NEG		
WEAR METALS		method	limit/base	-	historyd	history?
				current	history1	history2
ron	ppm	ASTM D5185m	>500	255		
Chromium	ppm		>3	2		
Nickel	ppm	ASTM D5185m	>3	0		
Fitanium Silver	ppm		>2	<1		
	ppm	ASTM D5185m ASTM D5185m	>2 >30	0 8		
Aluminum .ead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>103	0 <u> </u>		
in	ppm	ASTM D5185m	>5	4		
/anadium	ppm ppm	ASTM D5185m	>5	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base		history1	history2
Boron	ppm	ASTM D5185m		1		
Barium	ppm	ASTM D5185m		0		
Nolybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		4		
/lagnesium	ppm	ASTM D5185m		4		
Calcium	ppm	ASTM D5185m		3207		
hosphorus	ppm	ASTM D5185m		1105		
Zinc	ppm	ASTM D5185m		1240		
Sulfur	ppm	ASTM D5185m		9630		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>100	26		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
VISUAL		method	limit/base	current	history1	history2
Vhite Metal	scalar	*Visual	NONE	NONE		
ellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Gilt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
ppearance	scalar	*Visual	NORML	NORML		
Ddor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water 11:23) Rev: 1	scalar	*Visual		NEG	ation: MIKE WY	


Contact/Location: MIKE WYATT - TRANEW




## **OIL ANALYSIS REPORT**

🔺 Non-ferrous Metals





FLUID PROPERTIES limit/base history1 history2 method current Visc @ 40°C 95.6 cSt ASTM D445 SAMPLE IMAGES limit/base method current history1 history2 Color no image no image no image Bottom no image no image no image GRAPHS Ferrous Alloys 300 250 icke 200 E 150 100 50 Non-ferrous Metals 160 140 120 100 Md 80 60 40 20 0 Viscosity @ 40°C 130 125 120 115 110 () 00 € 105 र्द्छ 100 95 90 85 Abno 80 75 Apr1/24 Anr1/74



Contact/Location: MIKE WYATT - TRANEW