

OIL ANALYSIS REPORT

<u>|....||..||.|..|.................</u>

NORMAL

Machine Id

FRICK RDB 222 LO (S/N XA0400)

Refrigeration Compressor

USPI ALT-68 SC (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|----------|--------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | USP0007951 | USP0004898 | USP0001880 |
| Sample Date | | Client Info | | 03 Apr 2024 | 18 Jan 2024 | 26 Sep 2023 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | ATTENTION | NORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >8 | 10 | 13 | 10 |
| Chromium | ppm | ASTM D5185m | >2 | <1 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Lead | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Copper | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Tin | ppm | ASTM D5185m | >4 | <1 | 0 | <1 |
| Vanadium | ppm | ASTM D5185m | | 0 | <1 | <1 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Calcium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Phosphorus | ppm | ASTM D5185m | | 0 | 0 | 1 |
| Zinc | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 50 | 0 | 12 | 16 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | <1 | 0 | <1 |
| Sodium | ppm | ASTM D5185m | | 0 | <1 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 0 | 1 |
| Water | % | ASTM D6304 | >0.01 | 0.004 | 0.006 | 0.005 |
| ppm Water | ppm | ASTM D6304 | >100 | 48 | 67 | 55.2 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | | 1691 | 13412 | 1462 |
| Particles >6µm | | ASTM D7647 | >2500 | 430 | 4399 | 439 |
| Particles >14µm | | ASTM D7647 | >320 | 23 | 99 | 28 |
| Particles >21µm | | ASTM D7647 | >80 | 3 | 14 | 4 |
| Particles >38µm | | ASTM D7647 | >20 | 0 | 1 | 0 |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >/18/15 | 18/16/12 | 21/19/14 | 18/16/12 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D974 | 0.005 | 0.04 | 0.014 | 0.014 |


Contact/Location: MARK LONGING - TYSROG01




OIL ANALYSIS REPORT










| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.01 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 65.6 | 64.9 | 65.2 | 64.7 |
| SAMPLE IMAGES | | method | limit/base | current | history1 | history2 |
| Color | | | | HAS - RDB 222 AN AND 222 AN AND 223 AN AND 224 AN | • | |
| Bottom | | | | | | |



To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: F:

Contact/Location: MARK LONGING - TYSROG01 Page 2 of 2