

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

E-ONE LADDER 3 Component Hydraulic System

Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0906992		
Sample Date		Client Info		20 Mar 2024		
Machine Age	hrs	Client Info		7701		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	I	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	2		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>10	2		
Lead	ppm	ASTM D5185m	>10	2		
Copper	ppm	ASTM D5185m	>75	63		
Tin	ppm	ASTM D5185m	>10	2		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<1		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		5		
Calcium	ppm	ASTM D5185m		145		
Phosphorus	ppm	ASTM D5185m		529		
Zinc	ppm	ASTM D5185m		646		
Sulfur	ppm	ASTM D5185m		2854		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	2		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	<1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
		*Visual *Visual	NONE NONE	NONE NONE		
Silt	scalar					
Silt Debris	scalar scalar	*Visual	NONE	NONE		
Silt Debris Sand/Dirt	scalar scalar scalar	*Visual *Visual	NONE NONE	NONE LIGHT		
Silt Debris Sand/Dirt	scalar scalar scalar scalar	*Visual *Visual *Visual	NONE NONE	NONE LIGHT NONE		
Debris Sand/Dirt Appearance	scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual	NONE NONE NORML	NONE LIGHT NONE NORML	 	



OIL ANALYSIS REPORT



FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C cSi	t ASTM D445		37.0		
SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image
GRAPHS					
Ferrous Alloys					
9 - Iron 8 - Iron Iron 8 - Iron Iron					
7-					
E 5 -					
4					
2					
Mar20/24		Mar20/24 -			
≊ Non-ferrous Metals		Ma			
60 - REAL REAL FOR THE REAL FOR					
50					
40- 30-					
1					
20-					
10					
Mar20/24		Mar20/24 -			
		Mar			
Viscosity @ 40°C					
50 - Abnormal					
48 -					
46					
(C-0+) 44 45 42					
40 - Abnormal					
38 -					
36		4			
Mar20/24		Mar20/24			
2		2			
: WearCheck USA - 501 Ma			MIAI	MI VALLEY CAF	REER CENT
		Apr 2024 Apr 2024			6800 HOKE F GLEWOOD, (
: 10963804 D		Apr 2024 - Don	Baldridge		US 453
: FLEET	+ 1 000 007 1000				ontact: J SHA



JSHAW@MVCTC.COM T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Certificate L2367

Contact/Location: J SHAW - MIAENGOH Page 2 of 2