

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id

EP COMPOUND 800 BULK HEAD

Component New (Unused) Oil Fluid

{not provided} (--- GAL)

DIAGNOSIS

Recommendation


This is a baseline read-out on the submitted sample.


				Apr2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KFS0005056		
Sample Date		Client Info		03 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>5	<1		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>5	0		
Aluminum	ppm	ASTM D5185m	>5	2		
Lead	ppm	ASTM D5185m	>5	0		
Copper	ppm	ASTM D5185m	>5	0		
Tin	ppm	ASTM D5185m	>5	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		5		
Phosphorus	ppm	ASTM D5185m		166		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		9004		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.46		



OIL ANALYSIS REPORT







	VISUAL		method	limit/base	e current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
-	Sand/Dirt	scalar	*Visual	NONE	NONE		
Apr3/24	Appearance	scalar	*Visual	NORML	NORML		
Ř	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	e current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		743.9		
	Visc @ 100°C	cSt	ASTM D445		43.05		
	Viscosity Index (VI)	Scale	ASTM D2270		98		
+	SAMPLE IMAGES	5	method	limit/base	e current	history1	history2
Apr3.24	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metal	s		Apr3/24			
	Viscosity @ 40°C			Apr3/24	Acid Number		
entificate L2367 Unique Number Partificate L2367 Test Package Discuss this sample repor	: WearCheck USA - 50 : KFS0005056 r : 06139106 r : 10963914 e : IND 2 (Additional Tes	Rece Teste Diagi sts: FT-IF ice at 1-8	3 Doug Bogart	KIMBRO OIL COMPAN 2200 CLIFTON AV NASHVILLE, TI US 3720 Contact: CHRIS HIGGIN chiggins@kimbrooil.cor T: (270)305-134			

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)