

## **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

## EP COMPOUND 800 KOC COMPARTMENT 1

Component New (Unused) Oil Fluid

{not provided} (--- GAL)

## DIAGNOSIS

Recommendation


This is a baseline read-out on the submitted sample.


				Apr2024			
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		KFS0005057			
Sample Date		Client Info		03 Apr 2024			
Machine Age	hrs	Client Info		0			
Oil Age	hrs	Client Info		0			
Oil Changed		Client Info		N/A			
Sample Status				NORMAL			
CONTAMINATION		method	limit/base	current	history1	history2	
Water		WC Method		NEG			
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>5	<1			
Chromium	ppm	ASTM D5185m	>5	<1			
Nickel	ppm	ASTM D5185m	>5	0			
Titanium	ppm	ASTM D5185m		<1			
Silver	ppm	ASTM D5185m	>5	0			
Aluminum	ppm	ASTM D5185m	>5	2			
Lead	ppm	ASTM D5185m	>5	0			
Copper	ppm	ASTM D5185m	>5	0			
Tin	ppm	ASTM D5185m	>5	<1			
Vanadium	ppm	ASTM D5185m		<1			
Cadmium	ppm	ASTM D5185m		0			
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		0			
Barium	ppm	ASTM D5185m		0			
Molybdenum	ppm	ASTM D5185m		0			
Manganese	ppm	ASTM D5185m		0			
Magnesium	ppm	ASTM D5185m		<1			
Calcium	ppm	ASTM D5185m		4			
Phosphorus	ppm	ASTM D5185m		108			
Zinc	ppm	ASTM D5185m		0			
Sulfur	ppm	ASTM D5185m		5545			
CONTAMINANTS		method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>15	<1			
Sodium	ppm	ASTM D5185m		2			
Potassium	ppm	ASTM D5185m	>20	<1			
FLUID DEGRADA	TION	method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045		0.47			



## **OIL ANALYSIS REPORT**







	VISUAL		method	limit/bas	e current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Apr3/24 -	Appearance	scalar	*Visual	NORML	NORML			
Apı	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual		NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	IES	method	limit/bas	e current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445		749.9			
1	Visc @ 100°C	cSt	ASTM D445		43.25			
	Viscosity Index (VI)	Scale	ASTM D2270		98			
	SAMPLE IMAGES		method	limit/bas		history1	history2	
Apr3/24		<i>.</i>	method	IIIII/bus		motory i	Thotory 2	
2	Color					no image	no image	
	Bottom					no image	no image	
Andrew	Non-ferrous Metal	S		Apr3/24				
	Apr3/24			Apr3/24				
	Viscosity @ 40°C			mg KOH/g)	Acid Number			
				Acid	0.10		24	
Laboratory Sample No.	: WearCheck USA - 50 : KFS0005057		Madison Ave., Cary, NC 27513 Received : 04 Apr 2024 Tested : 04 Apr 2024			KIMBRO OIL COMPANY 2200 CLIFTON AVE		
Lab Number Unique Number	r : 06139107 r : 10963915 e : IND 2 ( Additional Tes <i>t, contact Customer Servi</i>	NASHVILLE, TI US 3720 Contact: CHRIS HIGGIN3 chiggins@kimbrooil.cor T: (270)305-134 2012) E						

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: CHRIS HIGGINS - KIMNAS Page 2 of 2

F: