

OIL ANALYSIS REPORT

INSOLUBLES

Machine Id

Press #6 Press #6

Component Hydraulic System Fluid KLUBER KLUBEROIL 4 UH1-46 N (220 GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

Contamination

MPC (Membrane Patch Colorimetry) test indicates a light concentration of varnish present. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is acceptable for this fluid.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PTK0005243	PTK0005249	PTK0005242
Sample Date		Client Info		29 Mar 2024	27 Feb 2024	26 Jan 2024
Machine Age	hrs	Client Info		22585	22003	21268
Oil Age	hrs	Client Info		4319	3737	3002
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				MARGINAL	MARGINAL	NORMAL
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	15	11	8
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	2	0	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		<1	0	0
Calcium	ppm	ASTM D5185m		11	6	1
Phosphorus	ppm	ASTM D5185m		137	124	128
Zinc	ppm	ASTM D5185m		13	3	<1
Sulfur	ppm	ASTM D5185m		0	0	4
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	3	2	2
Sodium	ppm	ASTM D5185m		0	1	0
Potassium	ppm	ASTM D5185m	>20	1	0	1
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	108	203	187
Particles >6µm		ASTM D7647	>1300	45	30	54
Particles >14µm		ASTM D7647	>160	7	2	7
Particles >21µm		ASTM D7647	>40	3	1	2
			10			0
Particles >38µm		ASTM D7647		0	0	0
Particles >38µm Particles >71µm Oil Cleanliness		ASTM D7647 ASTM D7647		0	0	0





OIL ANALYSIS REPORT












FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN) MPC Varnish Potential	mg KOH/g Scale	ASTM D8045 ASTM D7843	>15	0.558 🔺 31	0.413	0.062 10
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.2	46.4	46.4
SAMPLE IMAGES	6	method	limit/base	current	history1	history2

Color

Bottom




MPC



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: (909)239-7599 F:

Contact/Location: AJ ? - NIAPLE Page 2 of 4





Report Id: NIAPLE [WUSCAR] 06141286 (Generated: 04/15/2024 13:27:26) Rev: 1

Contact/Location: AJ ? - NIAPLE Page 3 of 4

This page left intentionally blank