

OIL ANALYSIS REPORT

SAMPLE INCODMATION

Area **RP-101** [10023985088] **B57008 - LOW LEVEL FEED SCREW**

Component Gearbox

Fluid PETRO CANADA PURITY FG EP GEAR FLUID 460 (--- QTS)

| D | IA(| ΒN | 0 | SI | S |
|---|-----|----|---|----------|----------|
| _ | | | ~ | <u> </u> | <u> </u> |

Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| | | ISO |
|---------------|---|-----|
| | | |
| | | ▲ |
| | | |
| | | |
| | | |
| | | |
| | | |
| | | |
| | | |
| p2016 Aug2017 | Sep2018 Aug2019 Sep2020 Aug2021 Sep2022 Dec2023 | |

Sample Rating Trend


| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|---------------|--------------|------------|-------------------|-----------------|-------------|
| Sample Number | | Client Info | | WC0894946 | WC06029351 | WC0781516 |
| Sample Date | | Client Info | | 07 Apr 2024 | 02 Dec 2023 | 22 May 2023 |
| Machine Age | mls | Client Info | | 0 | 0 | 0 |
| Oil Age | mls | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | ABNORMAL | ABNORMAL | ATTENTION |
| | N | method | limit/base | current | history1 | history2 |
| Water | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >200 | 9 | 4 | 9 |
| Chromium | ppm | ASTM D5185m | >15 | <1 | <1 | 0 |
| Nickel | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >25 | 2 | 1 | 0 |
| Lead | | ASTM D5185m | >25 | 2 | 0 | 0 |
| | ppm | | | 5 | 1 | 2 |
| Copper | ppm | ASTM D5185m | >200 | | | |
| Tin | ppm | ASTM D5185m | >25 | 8 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 14 | 17 | 20 |
| Barium | ppm | ASTM D5185m | | 0 | 3 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | | 2 | <1 | <1 |
| Calcium | ppm | ASTM D5185m | | 4 | <1 | 2 |
| Phosphorus | ppm | ASTM D5185m | 135 | 270 | 376 | 346 |
| Zinc | ppm | ASTM D5185m | | 60 | 23 | 11 |
| Sulfur | ppm | ASTM D5185m | 660 | 3951 | 5155 | 5088 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 4 | <1 | <1 |
| Sodium | ppm | ASTM D5185m | | 1 | 0 | 1 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 2 | 2 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | <u> </u> | ▲ 73153 | 11886 |
| Particles >6µm | | ASTM D7647 | >2500 | <u> </u> | ▲ 5020 | 1279 |
| Particles >14µm | | ASTM D7647 | >320 | 🔺 1551 | 120 | 30 |
| Particles >21µm | | ASTM D7647 | >80 | <u> </u> | 49 | 7 |
| Particles >38µm | | ASTM D7647 | >20 | 9 | 4 | 1 |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 1 | 1 |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | A 23/21/18 | ▲ 23/20/14 | 21/17/12 |
| FLUID DEGRADA | | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.54 | 1.39 | 1.24 | 1.63 |
| ·/2·/7) Boy: 1 | 39 | | - | | nation: RVAN LC | |


Report Id: HORAUS [WUSCAR] 06141313 (Generated: 04/15/2024 13:42:47) Rev: 1


Contact/Location: RYAN LOWE - HORAUS Page 1 of 2




OIL ANALYSIS REPORT











| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | LIGHT | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 460 | 387.0 | 344 | 365 |
| SAMPLE IMAGES | S | method | limit/base | current | history1 | history2 |
| Color | | | | | | |
| | | | | | | |

Bottom







Report Id: HORAUS [WUSCAR] 06141313 (Generated: 04/15/2024 13:42:47) Rev: 1

Contact/Location: RYAN LOWE - HORAUS

Page 2 of 2