

## **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id

## ATLAS COPCO API863474 - 4 OVER Component Compressor

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	<b>NATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06141406	UCH05212108	
Sample Date		Client Info		07 Apr 2024	23 Mar 2021	
Machine Age	hrs	Client Info		48224	21717	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	
Chromium	ppm	ASTM D5185m	>5	0	0	
Nickel	ppm	ASTM D5185m		0	<1	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>15	0	0	
Lead	ppm	ASTM D5185m	>65	0	0	
Copper	ppm	ASTM D5185m	>65	0	0	
Tin	ppm	ASTM D5185m	>10	0	0	
Antimony	ppm	ASTM D5185m			0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	1.5	0	0	
Barium	ppm	ASTM D5185m	0	0	<1	
Molybdenum	ppm	ASTM D5185m	0	0	<1	
Manganese	ppm	ASTM D5185m	0.3	0	0	
Magnesium	ppm	ASTM D5185m	0	0	0	
Calcium	ppm	ASTM D5185m	0	0	0	
Phosphorus	ppm	ASTM D5185m	406	8	11	
Zinc	ppm	ASTM D5185m	0	0	2	
Sulfur	ppm	ASTM D5185m	1283	0	28	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	28	14	
Sodium	ppm	ASTM D5185m		<1	<1	
Potassium	ppm	ASTM D5185m	>20	0	7	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.463	0.36	0.098	




# **OIL ANALYSIS REPORT**





	VISUAL		methoa	iimii/base	current	riistory i	riistoryz
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Apr7/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Ap	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	47.9	52.9	49.6	
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Apr7/24 +	Color						no image
	Bottom				A-		no image
	Non-ferrous Metal	S		Apr7/24			
	24 0 12/228 Viscosity @ 40°C			Apr7/24	Acid Number		
	(C) 50 (C) 50 (C			(B) 0.50 (B) 0.40 (B) 0.30 (B) 0.30 (B) 0.30 (B) 0.30 (B) 0.40 (B)	T Base		
	Abnormal			C	1.1		
	40 - 12/22 2 PM			Apr7/24	Mar23/21		



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: ELVIN DIAZ - UCAIRCAR

F: (201)342-6241