

OIL ANALYSIS REPORT

Sample Rating Trend

ISO

Machine Id KAESER SK 15T 2492697 (S/N 1087)

Component Compressor

Fluid KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA001774	KCP38422	KCP25923
Sample Date		Client Info		19 Mar 2024	01 Mar 2022	23 Jan 2020
Machine Age	hrs	Client Info		53696	47432	41303
Oil Age	hrs	Client Info		0	2000	3766
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				ABNORMAL	ATTENTION	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	1	0	1
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	<1	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>10	2	0	2
Lead	ppm	ASTM D5185m	>10	0	0	<1
Copper	ppm	ASTM D5185m		4	16	5
Tin	ppm	ASTM D5185m	>10	۰ ۱	0	0
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	PPIII			v	-	-
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	<1
Barium	ppm	ASTM D5185m	90	2	0	47
Molybdenum	ppm	ASTM D5185m	0	2	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	100	19	5	70
Calcium	ppm	ASTM D5185m	0	142	0	84
Phosphorus	ppm	ASTM D5185m	0	414	11	145
Zinc	ppm	ASTM D5185m	0	82	29	156
Sulfur	ppm	ASTM D5185m	23500	1070	18275	19480
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	2	2
Sodium	ppm	ASTM D5185m		23	4	39
Potassium	ppm	ASTM D5185m	>20	12	0	6
	ppm %	ASTM D5185m ASTM D6304	>20 >0.05	12 0.009	0 0.011	6 0.026
Water						
Water	% ppm	ASTM D6304	>0.05	0.009	0.011	0.026
Water ppm Water FLUID CLEANLIN	% ppm	ASTM D6304 ASTM D6304	>0.05 >500	0.009 95	0.011 110.7	0.026 264.4
Potassium Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm	% ppm	ASTM D6304 ASTM D6304 method	>0.05 >500 limit/base	0.009 95 current	0.011 110.7 history1	0.026 264.4 history2
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647	>0.05 >500 limit/base	0.009 95 current 9830	0.011 110.7 history1 5310	0.026 264.4 history2 9488
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647 ASTM D7647	>0.05 >500 limit/base >1300 >80	0.009 95 current 9830 ▲ 1630	0.011 110.7 history1 5310 1237	0.026 264.4 history2 9488 ▲ 2686
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647 ASTM D7647 ASTM D7647	>0.05 >500 limit/base >1300 >80	0.009 95 current 9830 ▲ 1630 ▲ 196	0.011 110.7 history1 5310 1237 111	0.026 264.4 history2 9488 2686 205
Water ppm Water FLUID CLEANLIN Particles >4µm	% ppm	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647	>0.05 >500 limit/base >1300 >80 >20 >4	0.009 95 current 9830 ▲ 1630 ▲ 196 ▲ 40	0.011 110.7 history1 5310 1237 111 35	0.026 264.4 history2 9488 ▲ 2686 ▲ 205 ▲ 57
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm	% ppm	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>0.05 >500 limit/base >1300 >80 >20 >4	0.009 95 current 9830 ▲ 1630 ▲ 196 ▲ 40 1	0.011 110.7 history1 5310 1237 1111 35 1	0.026 264.4 9488 2686 205 57 7
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm	% ppm ESS	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>0.05 >500 limit/base >1300 >80 >20 >4 >3	0.009 95 current 9830 ▲ 1630 ▲ 196 ▲ 40 1 0	0.011 110.7 history1 5310 1237 1111 35 1 0	0.026 264.4 9488 2686 205 57 7 3


Report Id: SEVANN [WUSCAR] 06142215 (Generated: 04/12/2024 00:25:26) Rev: 1


Contact/Location: Service Manager - SEVANN




OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	VLITE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45	50.7	49.3	▲ 57.79
SAMPLE IMAGES	;	method	limit/base	current	history1	history2
Color						
Bottom						





To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Test Package : IND 2 (Additional Tests: KF, PrtCount)

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: SEVANN [WUSCAR] 06142215 (Generated: 04/12/2024 00:25:26) Rev: 1

Certificate 12367

Contact/Location: Service Manager - SEVANN

T:

F:

Contact: Service Manager