

## **OIL ANALYSIS REPORT**

Sample Rating Trend

## NORMAL

## Area PALEXTRA 44 Machine to SULLIVAN PALATEK 21GE002322

Component Compressor

#### DIAGNOSIS

#### Recommendation

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCZ06143151		
Sample Date		Client Info		11 Mar 2024		
Machine Age	hrs	Client Info		10872		
Oil Age	hrs	Client Info		2000		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	13		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0		
Barium	ppm	ASTM D5185m	0.3	0		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m	0.3	<1		
Magnesium	ppm	ASTM D5185m	0.4	0		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	689	187		
Zinc	ppm	ASTM D5185m	0	51		
Sulfur	ppm	ASTM D5185m	1237	0		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.135	0.30		



# **OIL ANALYSIS REPORT**



	VISUAL		method	limit/base	e current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Marl 1/24	Appearance	scalar	*Visual	NORML	NORML		
Ma	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	e current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	44.62	52.8		
	SAMPLE IMAGES	5	method	limit/base	e current	history1	history2
Mar11/24 +	Color					no image	no image
	Bottom				0. (1) (1)	no image	no image
	Ferrous Alloys	s		Mart1/24			
	Viscosity @ 40°C			Mart 1/24	Acid Number		
	32 			Mar11/24	Mar11/24		Mar11/24
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report, Denotes test methods that	: 10967959 : IND 2 contact Customer Serve	Rece Teste Diagr ice at 1-8 7025 sco	ived : 09 ed : 10 nosed : 11 800-237-136 ope of accred	) Apr 2024 ) Apr 2024 Apr 2024 - An ). Jitation.	COMPRESSOR EQUIPMENT 227 AMBROSIO DR, SUITE / GURNEE, II US 6003 Contact: Rachel Pesnikov rachel.pesnikov@zornair.com T: (847)599-1333 6:2012) F: x		

Contact/Location: Rachel Pesnikov - UCZORGUR