


OIL ANALYSIS REPORT

Area **DF8** [8940] Machine Id

KAESER 1743-6010340 - WAPSIE VALLEY CREAMERY

Component



Sample Rating Trend



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		UDI06143183	UCH06043339	UCH05979855	
Sample Date		Client Info		02 Apr 2024	15 Dec 2023	05 Oct 2023	
Machine Age	hrs	Client Info		29044	27735	26852	
Oil Age	hrs	Client Info		1310	2181	1298	
Oil Changed		Client Info		Not Changd	Changed	Not Changd	
Sample Status				NORMAL	NORMAL	NORMAL	
CONTAMINATION		method	limit/base	current	history1	history2	
Water		WC Method	>0.05 NEG		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>50	0	0	0	
Chromium	ppm	ASTM D5185m	>10	0	0	0	
Nickel	ppm	ASTM D5185m	>3	0	0	0	
Titanium	ppm	ASTM D5185m	>3	0	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	0	
Aluminum	ppm	ASTM D5185m	>10	0	<1	0	
Lead	ppm	ASTM D5185m	>10	0	0	0	
Copper	ppm	ASTM D5185m	>50	23	9	4	
Tin	ppm	ASTM D5185m	>10	0	0	<1	
Vanadium	ppm	ASTM D5185m		0	0	0	
Cadmium	ppm	ASTM D5185m		0	0	0	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	1	0	0	0	
Barium	ppm	ASTM D5185m	0.3	0	0	0	
Molybdenum	ppm	ASTM D5185m	0	0	0	0	
Manganese	ppm	ASTM D5185m	0	<1	0	0	
Magnesium	ppm	ASTM D5185m	0	0	0	0	
Calcium	ppm	ASTM D5185m	0.5	0	0	0	
Phosphorus	ppm	ASTM D5185m	536	127	113	106	
Zinc	ppm	ASTM D5185m	0.2	60	25	4	
Sulfur	ppm	ASTM D5185m	649	290	565	768	
CONTAMINANTS		method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	0	0	0	
Sodium	ppm	ASTM D5185m		1	0	0	
Potassium	ppm	ASTM D5185m	>20	0	0	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045	0.337	0.32	0.22	0.23	



OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2


Visc @ 40°C	cSt	ASTM D445	42.0	42.9	44.8	43.3


SAMPLE IMAGES


Color


Bottom















Certificate 12367

Laboratory Sample No.

Lab Number : 06143183 Unique Number : 10967991 Test Package : IND 2

: UDI06143183

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 09 Apr 2024 **Tested** : 10 Apr 2024

Diagnosed : 11 Apr 2024 - Sean Felton

DELTA INDUSTRIES - CEDAR RAPIDS

6540 4TH ST SW UNIT A CEDAR RAPIDS, IA US 52404

Contact: MICHAEL FERRIS wearcheck@deltaind.net

T: (319)862-2500 F: (319)862-2501

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)