






KANSAS/44/EG - EXCAVATOR 20.529L [KANSAS^44^EG - EXCAVATOR]

Swing Drive Gear Case CAT TDTO 30W (--- GAL)





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The condition of the oil is acceptable for the time in service.


AL)				Apr2024		
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0901264		
Sample Date		Client Info		01 Apr 2024		
Machine Age	hrs	Client Info		23		
Oil Age	hrs	Client Info		23		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	5		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m		2		
Lead	ppm	ASTM D5185m		<1		
Copper	ppm	ASTM D5185m		<1		
Tin	ppm	ASTM D5185m		1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		5		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		22		
Calcium	ppm	ASTM D5185m	2980	3493		
Phosphorus	ppm	ASTM D5185m	1100	1006		
Zinc	ppm	ASTM D5185m	1270	1138		
Sulfur	ppm	ASTM D5185m		13325		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		15		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		





OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	100	90.9		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image











Certificate 12367

Laboratory

Sample No. : WC0901264 Lab Number : 06143420 Unique Number : 10968228

Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 09 Apr 2024

Tested : 10 Apr 2024 Diagnosed

: 10 Apr 2024 - Wes Davis

SHERWOOD CONSTRUCTION CO INC 3219 WEST MAY ST WICHITA, KS US 67213

Contact: BILL ORCUTT william.orcutt@wildcat.net

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: