

OIL ANALYSIS REPORT

Tin

NORMAL

Machine Id

TURBO EXPANDER

Hydraulic System MOBIL DTE OIL LIGHT (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

.............................

SAMPLE INFORMATION method WC0907819 WC0907813 WC0820286 Sample Number Client Info 09 Mar 2024 06 Feb 2024 Sample Date Client Info 04 Apr 2024 0 0 0 Machine Age hrs **Client Info** Oil Age hrs Client Info 0 0 0 Oil Changed **Client Info** N/A N/A N/A NORMAL Sample Status NORMAL NORMAL WEAR METALS ASTM D5185m >20 0 0 0 Iron ppm Chromium ppm ASTM D5185m >20 <1 0 <1 Nickel ppm ASTM D5185m >20 0 <1 <1 Titanium ASTM D5185m 0 <1 0 ppm Silver ppm ASTM D5185m 0 <1 0 Aluminum ppm ASTM D5185m >20 0 0 0 Lead ASTM D5185m >20 0 2 0 ppm ASTM D5185m >20 7 8 8 Copper ppm ppm ASTM D5185m >20 0 <1 0 Vanadium ASTM D5185m 0 <1 0 ppm Cadmium ppm ASTM D5185m 0 <1 0 0 0 0 Boron ppm ASTM D5185m Barium ppm ASTM D5185m 10 0 0 0 Molybdenum 1 0 ppm ASTM D5185m 0 Manganese ppm ASTM D5185m <1 <1 Magnesium ASTM D5185m 0 <1 <1 ppm 4 3 5 Calcium ppm ASTM D5185m Phosphorus ppm ASTM D5185m 100 96 106 Zinc ASTM D5185m 65 54 69 ppm Sulfur ASTM D5185m 488 463 453 ppm CONTAMINANTS Silicon ppm ASTM D5185m >15 0 <1 0 2 Sodium ppm ASTM D5185m 1 <1 Potassium ASTM D5185m >20 0 1 0 ppm >0.05 0.002 0.001 0.003 Water % ASTM D6304 ASTM D6304 >500 19 9 27 ppm Water ppm FLUID CLEANLINESS >5000 666 Particles >4µm ASTM D7647 594 533 >1300 105 128 Particles >6µm ASTM D7647 110 Particles >14µm ASTM D7647 >160 8 6 6 Particles >21µm ASTM D7647 >40 3 2 1 Particles >38µm ASTM D7647 >10 0 0 0 Particles >71µm ASTM D7647 >3 0 0 0

FLUID DEGRADATION Acid Number (AN)

Oil Cleanliness

mg KOH/g ASTM D8045

ISO 4406 (c)

>19/17/14

0.15

17/14/10

16/14/10

0.15


16/14/10


0.13


Contact/Location: JOE BARRETT - UGIMESWC





OIL ANALYSIS REPORT













			11 1.0			
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	31	33.1	33.1	33.1
SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Color				no image		
Bottom				no image		



: 10 Apr 2024

: 10 Apr 2024 - Wes Davis





* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Tested

Diagnosed

MESHOPPEN, PA US 18630 Contact: JOE BARRETT jbarrett@ugies.com T: F:

Report Id: UGIMESWC [WUSCAR] 06143705 (Generated: 04/10/2024 14:10:59) Rev: 1

Contact/Location: JOE BARRETT - UGIMESWC