

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area 385557 TRACE PO 37552 [38557] PAOTS0003-04082024TS3B

Hydraulic System

0001748229 CASTROL BRAYCO MICRONIC 889 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC06143772		
Sample Date		Client Info		08 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	0		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	0		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES	1-1-	method	limit/base	current	history1	history2
					· · · · · ·	· · · · · · · · · · · · · · · · · · ·
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		0		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		0		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	11		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304	>0.05	0.001		
ppm Water	ppm	ASTM D6304	>500	14		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles 5-15µm	count	*NAS 1638	>8000	2276		
Particles 15-25µm	count	*NAS 1638	>1425	310		
Particles 25-50µm	count	*NAS 1638	>253	83		
Particles 50-100µm	count	*NAS 1638	>45	0		
Particles >100µm	count	*NAS 1638	>8	0		
NAS 1638	Class	*NAS 1638	>5	4		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.085		



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.05	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		5.2		
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS						
Ferrous Alloys				Particle Coun	it	
iron			1,024	1 ⁰⁰⁰		12
o - chromium			512	.000-		-11
6			256	.000		-10
2				.000 -		-9
				.000-		-8
Apr8/24			Apr8/24 er 100 m	.000-		-7 - 6 - 5 - 4777777 -
			V led sa	,000 - ,000 Abnormal		-6 5
Non-ferrous Metals	5		lar.	N		-5 tramin
copper			ber of	,000		4 80
6- tin				,000		
<u>-</u>				,000		+2
2				500	1. A.	
24 12			124	250	< ···	0
Apr8/24			Apr8/24			
Viscosity @ 40°C				0 5-15μ 15-25μ Acid Number		-100μ > 100μ
Abnormal			, B ⁰			
0 + Abnormal				08		
0			.0 	06		
0-			and	02		
0				00-		
Apr8/24			Apr8/24	Apr8/24		Apr8/24
VearCheck USA - 501 VC06143772 <mark>6143772</mark>	Recei Teste	ved : 09 d : 12	, NC 27513 Apr 2024 2 Apr 2024	3	987 HAMPSTEA	ENGINEERING ID-MEXICO RD MPSTEAD, MD
0968580	Diagr		Apr 2024 - Jon	athan Hester	Contract: DET!!	US 21074
ND 2 (Additional Test					Contact: BETH	ANY HUGHES*

To discuss this sample report, contact Customer Service at 1-800-237-1369.

cSt (40°C)

:

:

÷

Laboratory

Sample No.

Lab Number

Unique Number Test Package

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: BETHANY HUGHES* - RIDHAM

Т:

F:

bethany@ridgeeng.com