

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KAESER 7540778

Component Compressor Fluid KAESER SIGMA (OEM) S-460 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA015995	KCPA005534	KCP55099
Sample Date		Client Info		26 Mar 2024	31 Jul 2023	16 Feb 2023
Machine Age	hrs	Client Info		8720	5363	3465
Oil Age	hrs	Client Info		3357	0	1091
Oil Changed		Client Info		Changed	N/A	Not Changd
Sample Status				NORMAL	NORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	3	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	10	9	6
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	0	13
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	90	2	7	48
Calcium	ppm	ASTM D5185m	2	0	<1	<1
Phosphorus	ppm	ASTM D5185m		0	3	0
Zinc	ppm	ASTM D5185m		0	2	12
Sulfur	ppm	ASTM D5185m		19598	20613	19358
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	<1
Sodium	ppm	ASTM D5185m		1	4	13
Potassium	ppm	ASTM D5185m	>20	0	1	5
Water	%	ASTM D6304	>0.05	0.007	0.011	0.026
ppm Water	ppm	ASTM D6304	>500	74	119.2	265.2
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		3565	686	6219
Particles >6µm		ASTM D7647	>1300	895	211	1830
Particles >14µm		ASTM D7647	>80	63	22	121
Particles >21µm		ASTM D7647	>20	19	4	931
Particles >38µm		ASTM D7647	>4	1	0	4
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	19/17/13	17/15/12	20/18/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.44	0.37	0.37


Contact/Location: Service Manager - AAOLON Page 1 of 2



OIL ANALYSIS REPORT








 4μm	~	
 .14µm	/ \	
 /		/
 /	- and the second	/

Certificate 12367

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.9	45.0	44.4
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color						-
Bottom				A.		\bigcirc



To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: AAOLON [WUSCAR] 06144258 (Generated: 04/12/2024 06:08:50) Rev: 1

Contact/Location: Service Manager - AAOLON Page 2 of 2

T:

F: