

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KAESER 7540772

Component Compressor Fluid KAESER SIGMA (OEM) S-460 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA015991	KCPA005508	KCP55446
Sample Date		Client Info		26 Mar 2024	31 Jul 2023	16 Feb 2023
Machine Age	hrs	Client Info		13526	10071	9450
Oil Age	hrs	Client Info		3365	0	2799
Oil Changed		Client Info		Not Changd	N/A	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>10	0	3	1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	11	11	9
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	0	<1
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	90	<1	<1	4
Calcium	ppm	ASTM D5185m	2	0	0	0
Phosphorus	ppm	ASTM D5185m		0	<1	0
Zinc	ppm	ASTM D5185m		0	0	5
Sulfur	ppm	ASTM D5185m		19474	20469	18266
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	<1
Sodium	ppm	ASTM D5185m		0	2	2
Potassium	ppm	ASTM D5185m	>20	0	0	0
Water	%	ASTM D6304		0.010	0.007	0.014
ppm Water	ppm	ASTM D6304	>500	110	74.2	147.5
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		4220	2659	6542
Particles >6µm		ASTM D7647	>1300	843	876	2064
Particles >14µm		ASTM D7647		26	60	1 73
Particles >21µm		ASTM D7647		6	16	4 3
Particles >38µm		ASTM D7647		0	0	1
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	19/17/12	19/17/13	2 0/18/15
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.45	0.40	0.39


Contact/Location: Service Manager - AAOLON Page 1 of 2



OIL ANALYSIS REPORT








Var29/22

NONE NONE NONE White Metal *Visual NONE scalar Yellow Metal *Visual NONE NONE NONE NONE scalar NONE Precipitate scalar *Visual NONE NONE NONE Silt scalar *Visual NONE NONE NONE NONE Debris *Visual NONE NONE LIGHT NONE scalar Sand/Dirt NONE NONE NONE NONE scalar *Visual NORML NORML NORML NORML Appearance scalar *Visual Odor *Visual NORML NORML NORML NORML scalar **Emulsified Water** scalar *Visual >0.05 NEG NEG NEG Free Water scalar *Visual NEG NEG NEG FLUID PROPERTIES Visc @ 40°C cSt ASTM D445 46 45.1 44.8 45.0 SAMPLE IMAGES Color

Bottom



To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F:

Report Id: AAOLON [WUSCAR] 06144271 (Generated: 04/12/2024 06:10:52) Rev: 1

Certificate 12367

Contact/Location: Service Manager - AAOLON Page 2 of 2