

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

B44736 (S/N 68934) Component Screw Compressor Fluid QUINCY QUINSYN F (30 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|---------------|--------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | WC0908022 | WC0846265 | WC0794800 |
| Sample Date | | Client Info | | 08 Apr 2024 | 10 Oct 2023 | 13 Apr 2023 |
| Machine Age | hrs | Client Info | | 0 | 16096 | 15302 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | Not Changd | Not Changd | Not Changd |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >60 | <1 | 1 | 0 |
| Chromium | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >5 | 0 | 0 | 0 |
| Lead | ppm | ASTM D5185m | >10 | <1 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >30 | <1 | <1 | 0 |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | <1 | 2 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | | 1 | <1 | 2 |
| Calcium | ppm | ASTM D5185m | | 4 | 70 | 2 |
| Phosphorus | ppm | ASTM D5185m | | 0 | 16 | 17 |
| Zinc | ppm | ASTM D5185m | | 0 | 4 | 0 |
| Sulfur | ppm | ASTM D5185m | | 209 | 29 | 0 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 3 | 2 | 2 |
| Sodium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | <1 | <1 | 0 |
| Water | % | ASTM D6304 | >0.1 | 0.006 | 0.002 | 0.005 |
| ppm Water | ppm | ASTM D6304 | >1000 | 63 | 20.7 | 50.3 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | 712 | 758 | 824 |
| Particles >6µm | | ASTM D7647 | >2500 | 94 | 113 | 172 |
| Particles >14µm | | ASTM D7647 | >320 | 8 | 13 | 12 |
| Particles >21µm | | ASTM D7647 | >80 | 2 | 5 | 2 |
| Particles >38µm | | ASTM D7647 | >20 | 0 | 1 | 0 |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | 17/14/10 | 17/14/11 | 17/15/11 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | .10 | 0.22 | 0.21 | 0.20 |


Contact/Location: PAT HUMPHREY - LLOSAIMN




OIL ANALYSIS REPORT







| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.1 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 42 | 50.1 | 49.6 | 49.0 |
| SAMPLE IMAGES | \$ | method | limit/base | current | history1 | history2 |
| Color | | | | | | |
| Bottom | | | | | | 60 |



Test Package : IND 2 (Additional Tests: KF, PrtCount) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: LLOSAIMN [WUSCAR] 06144300 (Generated: 04/22/2024 19:23:45) Rev: 1

Certificate 12367

Contact/Location: PAT HUMPHREY - LLOSAIMN

F: (651)688-6000

PAHumphrey@Hormel.com T: (651)905-8767