


# **OIL ANALYSIS REPORT**

Acid Number (AN)

mg KOH/g ASTM D8045

**ULTRA COOLANT [9246]** INGERSOLL RAND CBV688757 - UPS OASIS SUPPLY CORP Component





## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

## **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UDI06144372		
Sample Date		Client Info		02 Apr 2024		
Machine Age	hrs	Client Info		11831		
Oil Age	hrs	Client Info		38		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	1		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	<1		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0		
Barium	ppm	ASTM D5185m	500	1479		
Molybdenum	ppm	ASTM D5185m	0	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	0	1		
Calcium	ppm	ASTM D5185m	0	9		
Phosphorus	ppm	ASTM D5185m	20	<1		
Zinc	ppm	ASTM D5185m	0	8		
Sulfur	ppm	ASTM D5185m	200	511		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m		17		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.053



40

# **OIL ANALYSIS REPORT**




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TIES	method	limit/base	current	history1	history2

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

50.3

### **GRAPHS**


Visc @ 40°C




cSt

ASTM D445 49.4

copper																									
8 - sessessesses lead																									
6 - tin																									
4																									
2																									
0	_	_	-	-	_	_	_	-	-	_	-	_	-	-	_	_	-	-	_	-	-	-	-	_	
Apr2/24																									Anr7/74
Api																									Δn









Certificate 12367

Laboratory

**Sample No.** : UDI06144372 Lab Number : 06144372

Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Unique Number : 10969180

Received : 10 Apr 2024 Tested : 11 Apr 2024 Diagnosed : 12 Apr 2024 - Sean Felton

**DELTA INDUSTRIES - DOWNERS GROVE** 2201 CURTISS STREET DOWNERS GROVE, IL

US 60515 Contact: MICHAEL FERRIS

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (630)960-3931