



OIL ANALYSIS REPORT

Sample Rating Trend



DEGRADATION

Machine Id
4540-1
 Component
1 Gearbox
 Fluid
CASTROL RO 150 (--- GAL)

DIAGNOSIS

Recommendation

The oil is near the end of its useful service life, recommend schedule an oil change. Resample at the next service interval to monitor. Please note that this is a corrected copy for diagnostic comment updates per supplied limits.

Wear

The lead level is abnormal. All other component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is above the recommended limit.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0920086	---	---
Sample Date	Client Info		01 Apr 2024	---	---
Machine Age	mls	Client Info	71773	---	---
Oil Age	mls	Client Info	0	---	---
Oil Changed	Client Info		N/A	---	---
Sample Status			ABNORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >200	277	---	---
Chromium	ppm	ASTM D5185m >10	4	---	---
Nickel	ppm	ASTM D5185m >10	<1	---	---
Titanium	ppm	ASTM D5185m	<1	---	---
Silver	ppm	ASTM D5185m	0	---	---
Aluminum	ppm	ASTM D5185m >25	10	---	---
Lead	ppm	ASTM D5185m >50	▲ 8	---	---
Copper	ppm	ASTM D5185m >200	84	---	---
Tin	ppm	ASTM D5185m >10	0	---	---
Vanadium	ppm	ASTM D5185m	0	---	---
Cadmium	ppm	ASTM D5185m	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	7	---	---
Barium	ppm	ASTM D5185m	6	---	---
Molybdenum	ppm	ASTM D5185m	733	---	---
Manganese	ppm	ASTM D5185m	2	---	---
Magnesium	ppm	ASTM D5185m	23	---	---
Calcium	ppm	ASTM D5185m	150	---	---
Phosphorus	ppm	ASTM D5185m	1624	---	---
Zinc	ppm	ASTM D5185m	270	---	---
Sulfur	ppm	ASTM D5185m	17238	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >50	15	---	---
Sodium	ppm	ASTM D5185m	5	---	---
Potassium	ppm	ASTM D5185m >20	4	---	---


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	▲ 2.11	---	---




OIL ANALYSIS REPORT


▲ Non-ferrous Metals



▲ Non-ferrous Metals



Viscosity @ 40°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	MODER	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	155	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color				no image	no image	no image
Bottom				no image	no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0920086
Lab Number : 06145332
Unique Number : 10970140
Test Package : MOB 2

Received : 10 Apr 2024
Tested : 12 Apr 2024
Diagnosed : 20 Jun 2024 - Doug Bogart

ALSTOM C/O NEW JERSEY TRANSIT
 1148 NEWARK TURNPIKE
 KEARNY, NJ
 US 07032

Contact: DAVE GILBERT
 david.gilbert@alstomgroup.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (973)277-0826