


OIL ANALYSIS REPORT

SAMPLE INFORMATION method

Sample Rating Trend

limit/base



current

history1

history2

Machine Id **7800** Component **Hydraulic System** Fluid **MOBIL DTE 25 (120 GAL)**

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

A Wear

The copper level is abnormal. All other component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	NATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		PTK0005368	PTK0005038	PTK0004675			
Sample Date		Client Info		06 Apr 2024	20 Nov 2023	15 Aug 2023			
Machine Age	hrs	Client Info		22731	0	0			
Oil Age	hrs	Client Info		22731	0	0			
Oil Changed		Client Info		Not Changd	N/A	Not Changd			
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL			
CONTAMINATIO	N	method	limit/base	current	history1	history2			
Water		WC Method	>0.05	NEG	NEG	NEG			
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>20	<1	0	1			
Chromium	ppm	ASTM D5185m	>20	0	0	<1			
Nickel	ppm	ASTM D5185m	>20	0	<1	0			
Titanium	ppm	ASTM D5185m		0	0	<1			
Silver	ppm	ASTM D5185m		0	0	0			
Aluminum	ppm	ASTM D5185m	>20	0	<1	<1			
Lead	ppm	ASTM D5185m	>20	0	<1	1			
Copper	ppm	ASTM D5185m	>20	<u> </u>	A 30	▲ 34			
Tin	ppm	ASTM D5185m	>20	0	<1	<1			
Vanadium	ppm	ASTM D5185m		0	0	<1			
Cadmium	ppm	ASTM D5185m		0	0	<1			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		0	0	0			
Barium	ppm	ASTM D5185m		0	0	0			
Molybdenum	ppm	ASTM D5185m		20	24	28			
Manganese	ppm	ASTM D5185m		0	0	<1			
Magnesium	ppm	ASTM D5185m		70	2	6			
Calcium	ppm	ASTM D5185m		41	42	43			
Phosphorus	ppm	ASTM D5185m		432	366	386			
Zinc	ppm	ASTM D5185m		449	379	404			
Sulfur	ppm	ASTM D5185m		3512	2920	3515			
CONTAMINANTS	6	method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>15	2	2	2			
Sodium	ppm	ASTM D5185m		<1	<1	2			
Potassium	ppm	ASTM D5185m	>20	0	1	2			
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2			
Particles >4µm		ASTM D7647		665	864	1336			
Particles >6µm		ASTM D7647	>2500	124	170	564			
Particles >14µm		ASTM D7647	>320	10	9	51			
Particles >21µm		ASTM D7647	>80	3	2	11			
Particles >38µm		ASTM D7647	>20	0	0	0			
Particles >71µm		ASTM D7647	>4	0	0	0			
Oil Cleanliness		ISO 4406 (c)	>18/15	14/10	15/10	16/13			
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2			
Acid Number (AN)	mg KOH/g	ASTM D8045		0.51	0.32	0.32			
12:27) Rev: 1					Submitted	Submitted By: MIKE LEEN			
						Dava 1 -f			



OIL ANALYSIS REPORT

scalar

scalar

scalar

scalar

scalar

scalar

scalar

VISUAL

White Metal

Yellow Metal

Precipitate


Silt


Debris


Odor

Sand/Dirt


Appearance








Mar11/18 an 24/19







Laboratory Sample No. Certificate 12367

Aug 15/23

Emulsified Water Free Water	scalar scalar	*Visual *Visual	>0.05	NEG NEG	NEG NEG
FLUID PROPERTIES		method	limit/base	current	history
Visc @ 40°C	cSt	ASTM D445	44.2	44.5	45.1
SAMPLE IMAGES	6	method	limit/base	current	history
Color					•
Bottom					
GRAPHS					
Ferrous Alloys			491,52	Particle Coun	t

method

*Visual

*Visual

*Visual

*Visual

*Visual

*Visual

*Visual

scalar *Visual

limit/base

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

current

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

history1

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

history2

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML


history2

historv2

NEG

NEG

44.8



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GLEPRI [WUSCAR] 06145832 (Generated: 04/15/2024 11:12:27) Rev: 1

Submitted By: MIKE LEEN

F: (763)389-5352

Page 2 of 2