# OIL ANALYSIS REPORT

Sample Rating Trend


ISO

Machine Id
## CORD KING CORD KING 4045HF485
Component
**Hydraulic System**
Fluid
**{not provided} (--- GAL)**

## DIAGNOSIS

**Recommendation**
No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

**Wear**
All component wear rates are normal.

**Contamination**
There is a high amount of particulates present in the oil.

**Fluid Condition**
The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Sample Number | | Client Info | | **WC0843375** | --- | --- |
| Sample Date | | Client Info | | **28 Mar 2024** | --- | --- |
| Machine Age | hrs | Client Info | | **0** | --- | --- |
| Oil Age | hrs | Client Info | | **0** | --- | --- |
| Oil Changed | | Client Info | | **N/A** | --- | --- |
| Sample Status | | | | **ABNORMAL** | --- | --- |

| CONTAMINATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Water | | WC Method | >0.1 | **NEG** | --- | --- |

| WEAR METALS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Iron | ppm | ASTM D5185m | >20 | **4** | --- | --- |
| Chromium | ppm | ASTM D5185m | >10 | **<1** | --- | --- |
| Nickel | ppm | ASTM D5185m | >10 | **<1** | --- | --- |
| Titanium | ppm | ASTM D5185m | | **<1** | --- | --- |
| Silver | ppm | ASTM D5185m | | **0** | --- | --- |
| Aluminum | ppm | ASTM D5185m | >10 | **1** | --- | --- |
| Lead | ppm | ASTM D5185m | >10 | **4** | --- | --- |
| Copper | ppm | ASTM D5185m | >75 | **18** | --- | --- |
| Tin | ppm | ASTM D5185m | >10 | **2** | --- | --- |
| Vanadium | ppm | ASTM D5185m | | **<1** | --- | --- |
| Cadmium | ppm | ASTM D5185m | | **<1** | --- | --- |

| ADDITIVES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Boron | ppm | ASTM D5185m | | **0** | --- | --- |
| Barium | ppm | ASTM D5185m | | **0** | --- | --- |
| Molybdenum | ppm | ASTM D5185m | | **1** | --- | --- |
| Manganese | ppm | ASTM D5185m | | **<1** | --- | --- |
| Magnesium | ppm | ASTM D5185m | | **2** | --- | --- |
| Calcium | ppm | ASTM D5185m | | **81** | --- | --- |
| Phosphorus | ppm | ASTM D5185m | | **430** | --- | --- |
| Zinc | ppm | ASTM D5185m | | **506** | --- | --- |
| Sulfur | ppm | ASTM D5185m | | **3369** | --- | --- |

| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Silicon | ppm | ASTM D5185m | >20 | **2** | --- | --- |
| Sodium | ppm | ASTM D5185m | | **0** | --- | --- |
| Potassium | ppm | ASTM D5185m | >20 | **1** | --- | --- |

| FLUID CLEANLINESS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Particles >4µm | | ASTM D7647 | >5000 | ▲ **60018** | --- | --- |
| Particles >6µm | | ASTM D7647 | >1300 | ▲ **6076** | --- | --- |
| Particles >14µm | | ASTM D7647 | >160 | ▲ **261** | --- | --- |
| Particles >21µm | | ASTM D7647 | >40 | ▲ **70** | --- | --- |
| Particles >38µm | | ASTM D7647 | >10 | **4** | --- | --- |
| Particles >71µm | | ASTM D7647 | >3 | **0** | --- | --- |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | ▲ **23/20/15** | --- | --- |

| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | **0.40** | --- | --- |

# OIL ANALYSIS REPORT

Particle Trend




Base Number




Acid Number




Viscosity @ 40°C




Base Number




| VISUAL | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| White Metal | scalar | *Visual | NONE | **NONE** | --- | --- |
| Yellow Metal | scalar | *Visual | NONE | **NONE** | --- | --- |
| Precipitate | scalar | *Visual | NONE | **NONE** | --- | --- |
| Silt | scalar | *Visual | NONE | **NONE** | --- | --- |
| Debris | scalar | *Visual | NONE | **NONE** | --- | --- |
| Sand/Dirt | scalar | *Visual | NONE | **NONE** | --- | --- |
| Appearance | scalar | *Visual | NORML | **NORML** | --- | --- |
| Odor | scalar | *Visual | NORML | **NORML** | --- | --- |
| Emulsified Water | scalar | *Visual | >0.1 | **NEG** | --- | --- |
| Free Water | scalar | *Visual | | **NEG** | --- | --- |

| FLUID PROPERTIES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Visc @ 40°C | cSt | ASTM D445 | | **42.7** | --- | --- |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|
| Color | | |  | *no image* | *no image* |
| Bottom | | |  | *no image* | *no image* |

GRAPHS

Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C


Particle Count




Acid Number




**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513
**Sample No.** : WC0843375 **Received** : 11 Apr 2024
**Lab Number** : 06146536 **Tested** : 15 Apr 2024
**Unique Number** : 10976614 **Diagnosed** : 15 Apr 2024 - Don Baldridge
**Test Package** : MOB 2 ( Additional Tests: TBN )

Certificate L2367

*To discuss this sample report, contact Customer Service at 1-800-237-1369.*
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
*Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)*

**PARKE CO FIREWOOD**
4121 N 100 E
MARSHALL, IN
US 47859
Contact: ELAM SWAREY JR
cealey@cebridge.net
T: (765)597-2237
F: