

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

LIEBHERR 1400 CR4415 (S/N 074-414)

Component Front Right Planetary

GEAR OIL ISO 220 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Woor

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.


				Apr2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0892988		
Sample Date		Client Info		05 Apr 2024		
Machine Age	hrs	Client Info		11100		
Oil Age	hrs	Client Info		1000		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	85		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>75	0		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m	>10	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	0		
Barium	ppm	ASTM D5185m	15	0		
Molybdenum	ppm	ASTM D5185m	15	0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	50	0		
Calcium	ppm	ASTM D5185m	50	0		
Phosphorus	ppm	ASTM D5185m	350	564		
Zinc	ppm	ASTM D5185m	100	0		
Sulfur	ppm	ASTM D5185m	12500	1916		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	21		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	8		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		




OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	220	215		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image



Non-ferrous Metals





Certificate 12367

Laboratory

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0892988 Lab Number : 06146801 Unique Number : 10976879

Test Package : CONST

Received : 11 Apr 2024 Tested : 12 Apr 2024

Diagnosed : 15 Apr 2024 - Sean Felton

BUCKNER - WILLIS 18123 HWY 75 NORTH

WILLIS, TX US 77378

Contact: JOHN HAWKINS johnh@bucknercompanies.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: