




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
VOLVO A30G 742602
 Component
Diesel Engine
 Fluid
CHEVRON 15W40 (10 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		ML0001165	VCP426169	VCP393479
Sample Date	Client Info		08 Apr 2024	11 Sep 2023	23 Feb 2023
Machine Age	hrs	Client Info	4529	3908	3404
Oil Age	hrs	Client Info	4529	0	0
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>6.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	11	7	7
Chromium	ppm	ASTM D5185m >20	<1	<1	0
Nickel	ppm	ASTM D5185m >2	1	<1	0
Titanium	ppm	ASTM D5185m	2	<1	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >25	2	2	2
Lead	ppm	ASTM D5185m >40	2	<1	<1
Copper	ppm	ASTM D5185m >330	4	<1	<1
Tin	ppm	ASTM D5185m >15	2	<1	<1
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	<1	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	403	313	269
Barium	ppm	ASTM D5185m	<1	0	0
Molybdenum	ppm	ASTM D5185m	84	82	118
Manganese	ppm	ASTM D5185m	1	<1	<1
Magnesium	ppm	ASTM D5185m	354	384	608
Calcium	ppm	ASTM D5185m	1432	1493	1559
Phosphorus	ppm	ASTM D5185m	1096	966	726
Zinc	ppm	ASTM D5185m	1161	1165	957
Sulfur	ppm	ASTM D5185m	3463	3611	2908

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	5	5	6
Sodium	ppm	ASTM D5185m >50	0	<1	2
Potassium	ppm	ASTM D5185m >20	2	<1	2




INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.4	0.3	0.4
Nitration	Abs/cm	*ASTM D7624 >20	7.5	7.1	8.0
Sulfation	Abs/.1mm	*ASTM D7415 >30	21.9	20.8	22.9

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.3	14.5	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	6.7	7.0	7.4





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	12.2	12.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ML0001165 **Received** : 12 Apr 2024
Lab Number : 06146889 **Tested** : 15 Apr 2024
Unique Number : 10976967 **Diagnosed** : 15 Apr 2024 - Sean Felton
Test Package : CONST (Additional Tests: TBN)

PLEASANT EXCAVATING COMPANY INC
 24024 FREDERICK ROAD
 CLARKSBURG, MD
 US 20871
 Contact: H TRENT
 HTRENT@PLEASANTS.ORG
 T: (301)252-5635
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)