

# **OIL ANALYSIS REPORT**

Sample Rating Trend

**NORMAL** 



**EX-401** Component

Diesel Engine

Machine Id

CITGO CITGUARD 600 15W40 (--- GAL)

## Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.


## Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

				Mar2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0909419		
Sample Date		Client Info		19 Mar 2024		
Machine Age	hrs	Client Info		3784		
Oil Age	hrs	Client Info		500		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	18		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m		0		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m		8		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	13	0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m	57	65		
Manganese	ppm	ASTM D5185m	07	0		
Magnesium	ppm	ASTM D5185m	825	1037		
Calcium	ppm	ASTM D5185m	1100	1291		
Phosphorus	ppm	ASTM D5185m	933	1128		
Zinc	ppm	ASTM D5185m	1089	1326		
Sulfur	ppm	ASTM D5185m	2769	3702		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	<1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3		
Nitration	Abs/cm	*ASTM D7624	>20	9.9		
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.7		
FLUID DEGRADA	TION _	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5		
Base Number (BN)	mg KOH/g	ASTM D2896	11.0	7.2		
Dago Hambor (DN)	nig Norlig	7.0 TW D2000	. 1.0	1.2		




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPER	TIES	method	limit/base	current	historv1	history2

FLUID FROFER	IIIES	memou			HISTOLAL	HISTOLYZ
Visc @ 100°C	cSt	ASTM D445	15.4	12.5		



10	Non Terrous Metals	
10		
	copper	
8	presentation   Gad	
0	annonnenne till	
6		
Ε		
mdd		
4		
2	•	
0		
	24	24
	761	9/
	Mar19/24	Mar19/24
		2
	Viscosity @ 100°C	
	. =	









Certificate 12367

Laboratory Sample No.

: WC0909419 Lab Number : 06146964 Unique Number : 10977042 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Apr 2024 Tested Diagnosed

: 15 Apr 2024 : 15 Apr 2024 - Wes Davis

E.C. PACE CO. 1811 HOLLINS RD. ROANOKE, VA US 24012 Contact: EDDIE SECO ESECO@ECPACE.COM

T: (276)266-5849

F: (540)343-6909

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)