


OIL ANALYSIS REPORT

SAMPLE INFORMATION method

Sample Rating Trend

limit/base



history1

current

history2

Machine Id

COMP 6 Component Air Compressor

Fluid {not provided} (--- QTS)

DIAGNOSIS

Recommendation

We recommend that you drain the oil from the component if this has not already been done. Resample at the next service interval to monitor. Please specify the brand and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is above the recommended limit. Confirmed.


| SAIVIFLE INFOR | VIATION | methou | IIIIII/Dase | current | TISLOTYT | TIStory2 |
|------------------|----------|--------------|-------------|---------------|-------------|-------------|
| Sample Number | | Client Info | | USP227735 | USP227743 | USP227698 |
| Sample Date | | Client Info | | 11 Apr 2024 | 28 Nov 2023 | 07 Nov 2023 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | ABNORMAL | NORMAL | ABNORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >50 | 4 | <1 | 0 |
| Chromium | ppm | ASTM D5185m | >4 | <1 | <1 | 0 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >10 | 1 | 2 | 0 |
| Lead | ppm | ASTM D5185m | >20 | 1 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >40 | 3 | 2 | 6 |
| Tin | ppm | ASTM D5185m | >5 | 1 | <1 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | 1 | <1 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | | <1 | 4 | 0 |
| Molybdenum | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | | 1 | <1 | 0 |
| Calcium | ppm | ASTM D5185m | | 0 | 1 | 0 |
| Phosphorus | ppm | ASTM D5185m | | 0 | 1 | 1 |
| Zinc | ppm | ASTM D5185m | | 5 | 0 | 14 |
| Sulfur | ppm | ASTM D5185m | | 31 | 0 | 0 |
| CONTAMINANTS | 6 | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 0 | <1 | 0 |
| Sodium | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 2 | 0 |
| Water | % | ASTM D6304 | >0.6 | 0.017 | 0.011 | 0.022 |
| ppm Water | ppm | ASTM D6304 | >6000 | 171 | 117 | 226.9 |
| FLUID CLEANLIN | NESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | 1843 | 1705 | |
| Particles >6µm | | ASTM D7647 | | 685 | 312 | |
| Particles >14µm | | ASTM D7647 | >320 | 120 | 58 | |
| Particles >21µm | | ASTM D7647 | >80 | 49 | 23 | |
| Particles >38µm | | ASTM D7647 | >20 | 3 | 3 | |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 0 | |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | 18/17/14 | 18/15/13 | |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | A 2.75 | 0.25 | 1.95 |
| | | | | | | |


Contact/Location: JOE ROSENFIELD - CARFORCOL Page 1 of 2



OIL ANALYSIS REPORT








| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | 🔺 MODER |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.6 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | | 51.9 | 46.2 | 53.53 |
| SAMPLE IMAGES | 6 | method | limit/base | current | history1 | history2 |
| Color | | | | . 6 | . 6. | |

Bottom



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: CARFORCOL [WUSCAR] 06147349 (Generated: 04/15/2024 19:22:08) Rev: 1

Certificate 12367

Contact/Location: JOE ROSENFIELD - CARFORCOL

F: