

OIL ANALYSIS REPORT

DEGRADATION

Machine Id

GARDNER DENVER 7 (S/N S541933)

Component Compressor Fluid

USPI COMP CLEAN II (--- GAL)

DIAGNOSIS

Recommendation

The oil is near the end of it's useful service life, recommend schedule an oil change. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is at the top-end of the recommended limit.


	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USPM36679	USPM30146	USP0001063
Sample Date		Client Info		11 Apr 2024	26 Feb 2024	19 Jul 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	SEVERE	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	3	0	0
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m		<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	1	0	0
Lead	ppm	ASTM D5185m	>25	1	0	0
Copper	ppm		>50	4	5	4
Tin	ppm	ASTM D5185m	>15	1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	0	1
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m		<1	<1	0
Calcium	ppm	ASTM D5185m		0	<1	3
Phosphorus	ppm	ASTM D5185m		0	0	0
Zinc	ppm	ASTM D5185m		14	4	5
Sulfur	ppm	ASTM D5185m		0	0	0
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	0
Sodium	ppm	ASTM D5185m		0	0	0
	nom					
Potassium	ppm	ASTM D5185m	>20	<1	2	1
	%	ASTM D5185m ASTM D6304		<1 0.033	2 0.021	1 0.019
Water			>0.1			
Water	% ppm	ASTM D6304	>0.1	0.033	0.021	0.019
Water ppm Water FLUID CLEANLIN	% ppm	ASTM D6304 ASTM D6304	>0.1 >1000	0.033 336 current 1350	0.021 218	0.019 193.1
Water ppm Water FLUID CLEANLIN Particles >4μm Particles >6μm	% ppm	ASTM D6304 ASTM D6304 method	>0.1 >1000 limit/base >10000	0.033 336 current	0.021 218 history1	0.019 193.1 history2
Potassium Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647	>0.1 >1000 limit/base >10000 >2500	0.033 336 current 1350	0.021 218 history1 983	0.019 193.1 history2 2455
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647 ASTM D7647	>0.1 >1000 limit/base >10000 >2500 >320	0.033 336 current 1350 400	0.021 218 history1 983 188	0.019 193.1 history2 2455 172
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm	% ppm	ASTM D6304 ASTM D6304 method ASTM D7647 ASTM D7647 ASTM D7647	>0.1 >1000 limit/base >10000 >2500 >320	0.033 336 current 1350 400 51	0.021 218 history1 983 188 14	0.019 193.1 history2 2455 172 9
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm	% ppm	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647	>0.1 >1000 limit/base >10000 >2500 >320 >80 >20	0.033 336 current 1350 400 51 21	0.021 218 history1 983 188 14 5	0.019 193.1 history2 2455 172 9 2
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm	% ppm	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>0.1 >1000 limit/base >10000 >2500 >320 >80 >20	0.033 336 current 1350 400 51 21 2	0.021 218 history1 983 188 14 5 1	0.019 193.1 2455 172 9 2 0
Water ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm	% ppm JESS	ASTM D6304 ASTM D6304 Method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>0.1 >1000 limit/base >10000 >2500 >320 >320 >80 >20 >4	0.033 336 current 1350 400 51 21 2 2 0	0.021 218 history1 983 188 14 5 1 1 0	0.019 193.1 2455 172 9 2 0 0 0





OIL ANALYSIS REPORT












VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		41.9	▲ 57.5	47.3
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color						

Bottom



: 15 Apr 2024

: 15 Apr 2024 - Doug Bogart



T:

F:

Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Lab Number : 06147352

Unique Number : 10977430

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Tested

Diagnosed

Report Id: CARFORCO [WUSCAR] 06147352 (Generated: 04/15/2024 19:22:44) Rev: 1

Certificate 12367

Contact/Location: ? ? - CARFORCO Page 2 of 2