

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

FES TYSNRH B105 (S/N 2512595)

Refrigeration Compressor

USPI 1009-68 SC (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

w2013 New2014 May2016 Des2017 Jul2019 Osc2020 Jan 2022 Apr2023						
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0006745	USP0004982	USP0001221
Sample Date		Client Info		11 Apr 2024	15 Jan 2024	15 Oct 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	<1	0	0
Chromium	ppm	ASTM D5185m	>2	<1	<1	0
Nickel	ppm	ASTM D5185m		<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	1	0	0
Lead	ppm	ASTM D5185m	>2	1	0	<1
Copper	ppm	ASTM D5185m	>8	<1	0	0
Tin	ppm	ASTM D5185m	>4	1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m		<1	0	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		0	0	0
Zinc	ppm	ASTM D5185m		0	0	<1
Sulfur	ppm	ASTM D5185m	50	0	0	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	3	3	2
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
Water	%	ASTM D6304	>0.01	0.005	0.003	0.007
ppm Water	ppm	ASTM D6304	>100	57	27	70.0
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	821	2068	1277
Particles >6µm		ASTM D7647	>2500	187	475	243
Particles >14μm		ASTM D7647	>320	12	24	11
Particles >21µm		ASTM D7647	>80	4	4	3
Particles >38µm		ASTM D7647	>20	0	0	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	17/15/11	18/16/12	17/15/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
A - ! - N (A N)		A OTA 4 DOZ 4	0.005	0.014	0.044	0.040

Acid Number (AN)

0.014


0.014


mg KOH/g ASTM D974 0.005


0.013





OIL ANALYSIS REPORT












VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FILLID DDODEDI			11 11 11			

FLUID PROPER	THES	method	iimii/base	current	nistory i	nistory∠
Visc @ 40°C	cSt	ASTM D445	67	65.3	65.6	64.9

Color	











Certificate 12367

Laboratory Sample No.

Lab Number : 06147369

: USP0006745 Unique Number : 10977447

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Apr 2024

Tested : 15 Apr 2024 Diagnosed : 15 Apr 2024 - Doug Bogart

TYSON-NORTH RICHLAND HILLS-USP

6350 BLOWN CT NORTH RICHLAND HILLS, TX US 76180

Contact: JOHN MORGAN

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: (817)514-3519 F:

Report Id: TYSNORTX [WUSCAR] 06147369 (Generated: 04/15/2024 20:48:40) Rev: 1

Test Package : IND 2

Contact/Location: JOHN MORGAN - TYSNORTX