

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

MACHINE 18 (S/N 202505-5-056) Gearbox

Fluid MOBIL MOBILGEAR SHC 320 (12 GAL)

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The oil viscosity is lower than normal. Confirm oil type. The AN level is acceptable for this fluid.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0910082		
Sample Date		Client Info		01 Apr 2024		
Machine Age	mths	Client Info		0		
Oil Age	mths	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				ATTENTION		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	12		
Chromium	ppm	ASTM D5185m	>15	<1		
Nickel	ppm	ASTM D5185m	>15	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>100	<1		
Copper	ppm	ASTM D5185m	>200	2		
Tin	ppm	ASTM D5185m	>25	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		104		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		16		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		147		
Phosphorus	ppm	ASTM D5185m		683		
Zinc	ppm	ASTM D5185m		84		
Sulfur	ppm	ASTM D5185m		16320		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	19		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		1.31		



Apr1/24 0.0

58

OIL ANALYSIS REPORT



Apr1/24

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	171		
SAMPLE IMAGES	2	mothod	limit/base	ourront	history1	history?
SAMPLE IMAGES	5	method	IIIIII/Dase	current	history1	history2
Color					no image	no image
Bottom					no image	no image
h h h h h h h h h h h h h h h h h h h			Apri/24			
Non-ferrous Metal	S		Apr1/24			
Viscosity @ 40°C				Acid Number		
Abnormal			(B/)	5		
Abnormal			1 Burn Burn Burn Burn Burn Burn Burn Burn	5-		
April24			Apr1/24	Apri/24		
VearCheck USA - 50 VC0910082 6147503 0977581 VD 2	1 Madiso Recei Teste Diagn	ved : 12 d : 15	r, NC 27513 2 Apr 2024 5 Apr 2024 Apr 2024 - Dor		CITY OF I L	SON - Plant 130 MUELSON S NDUSTRY, C IS 91748-12 Ict: ERIC LOY

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: CONSAM [WUSCAR] 06147503 (Generated: 04/16/2024 12:25:50) Rev: 1

Certificate L2367

Laboratory

Sample No.

Lab Number Unique Number Test Package

> Contact/Location: ERIC LOYA - CONSAM Page 2 of 2

т:

F: