


OIL ANALYSIS REPORT

Sample Rating Trend





3077 Component **Transmission (Manual)** Fluid **CONOCO PHILLIPS GUARDOL ECT 15W40 (--- GAL)**

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Area [22887] Machine Id

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0836138	WC0836234	WC0802438
Sample Date		Client Info		10 Apr 2024	01 Dec 2023	01 Aug 2023
Machine Age	hrs	Client Info		4653	4238	3625
Oil Age	hrs	Client Info		529	2238	520
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	4	13	12
Chromium	ppm	ASTM D5185m	>5	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>7	0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	<1	0
Lead	ppm	ASTM D5185m	>45	1	3	1
Copper	ppm	ASTM D5185m	>225	5	14	12
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	85	99	<1	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		2	<1	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	350	595	5	6
Calcium	ppm	ASTM D5185m	1800	1232	220	231
Phosphorus	ppm	ASTM D5185m	1000	1081	642	639
Zinc	ppm	ASTM D5185m	1100	1213	836	808
Sulfur	ppm	ASTM D5185m	3500	3940	1728	2007
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>125	7	5	4
Sodium	ppm	ASTM D5185m		<1	0	0
Potassium	ppm	ASTM D5185m	>20	4	2	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
3:17:54) Rev: 1					omitted By: JAM	ES STEELMON



OIL ANALYSIS REPORT



FLUID PROPEF Visc @ 40°C	cSt	method ASTM D445	limit/base	current 74.8	history1 55.3	hist 59.3
SAMPLE IMAG	ES	method	limit/base	current	history1	hist
Color				na imaga	no (more)	no in
Color				no image	no image	no in
Bottom				no image	no image	no in
GRAPHS						
Ferrous Alloys						
4 iron						
2 - chromium						
0-		$\langle \rangle$				
8						
6-			$\mathbf{\lambda}$			
4						
2-						
0			4			
Feb10/22 Mar6/23	Aug1/23	Dec1/23	Apr10/24 -			
Non-ferrous Met			4			
		\sim				
2 - copper		\sim				
0-		\sim				
8 -						
6 -						
4						
2	The Real Property lies in the Party name	ARRANGE STATE				
	~					
Feb10/22 -	Aug1/23 -	Dec1/23	Apr10/24			
۳ – Viscosity @ 40°			A			
Base						
0-						
D -						
D						
Abnormal			-			
0		/				
		\checkmark				
		23 +	24+			
	1/2	-	0			
Feb10/22	Aug1/23	Dec1/23	Apr10/24			



Report Id: MANTUL [WUSCAR] 06148191 (Generated: 04/15/2024 13:17:54) Rev: 1

Submitted By: JAMES STEELMON

Page 2 of 2